

## SABIC Innovative Plastics Lexan® EXL1132T PC Copolymer

Category : Polymer , Thermoplastic , Polycarbonate (PC)

### Material Notes:

Lexan® EXL1132T polycarbonate (PC) siloxane copolymer resin is a UV stabilized transparent injection molding (IM) grade with extra release properties. This resin offers good low temperature (-20 C) ductility in combination with high flow characteristics and excellent processability with opportunities for shorter IM cycle times compared to standard PC resins. Lexan EXL1132T resin is a general purpose product available in transparent and opaque colors and may be an excellent candidate for a broad range of applications.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-Lexan-EXL1132T-PC-Copolymer.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-EXL1132T-PC-Copolymer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.19 g/cc	1.19 g/cc	ASTM D792
Density	1.19 g/cc	0.0430 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption	0.0900 %	0.0900 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.12 %	0.12 %	ISO 62
Linear Mold Shrinkage, Flow	0.0040 - 0.0080 cm/cm @Thickness 3.20 mm	0.0040 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0040 - 0.0080 cm/cm @Thickness 3.20 mm	0.0040 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	20 g/10 min @Load 1.20 kg, Temperature 300 °C	20 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238
Melt Index of Compound	19 g/10 min @Load 1.20 kg, Temperature 300 °C	19 g/10 min @Load 2.65 lb, Temperature 572 °F	MVR [cm <sup>3</sup> /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell L	89	89	ISO 2039-2
Tensile Strength at Break	56.0 MPa	8120 psi	50 mm/min; ISO 527
	57.0 MPa	8270 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	57.0 MPa	8270 psi	50 mm/min; ISO 527
	58.0 MPa	8410 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	117.9 %	117.9 %	Type I, 50 mm/min; ASTM D638

Mechanical Properties	119.4 % Metric	119.4 % English	50 mm/min; ISO 527 Comments
Elongation at Yield	5.4 %	5.4 %	50 mm/min; ISO 527
	5.7 %	5.7 %	Type I, 50 mm/min; ASTM D638
Tensile Modulus	2.26 GPa	328 ksi	50 mm/min; ASTM D638
	2.34 GPa	339 ksi	1 mm/min; ISO 527
Flexural Yield Strength	89.0 MPa	12900 psi	2 mm/min; ISO 178
	94.0 MPa	13600 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.14 GPa	310 ksi	2 mm/min; ISO 178
	2.24 GPa	325 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	7.36 J/cm	13.8 ft-lb/in	ASTM D256
	6.18 J/cm	11.6 ft-lb/in	ASTM D256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Notched (ISO)	55.0 kJ/m <sup>2</sup>	26.2 ft-lb/in <sup>2</sup>	80*10*3; ISO 180/1A
	40.0 kJ/m <sup>2</sup>	19.0 ft-lb/in <sup>2</sup>	80*10*3; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Unnotched (ISO)	NB	NB	80*10*3; ISO 180/1U
	NB	NB	80*10*3; ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	6.50 J/cm <sup>2</sup>	30.9 ft-lb/in <sup>2</sup>	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	4.50 J/cm <sup>2</sup>	21.4 ft-lb/in <sup>2</sup>	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Dart Drop, Total Energy	74.0 J	54.6 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
	74.8 µm/m-°C	41.6 µin/in-°F	

Thermal Properties	Metric	English	Comments
	@Temperature -40.0 - 95.0 °C	@Temperature -40.0 - 203 °F	
	74.8 µm/m-°C	41.6 µin/in-°F	
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	ISO 11359-2
CTE, linear, Transverse to Flow	76.4 µm/m-°C	42.4 µin/in-°F	
	@Temperature -40.0 - 95.0 °C	@Temperature -40.0 - 203 °F	ASTM E 831
	76.4 µm/m-°C	42.4 µin/in-°F	
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	ISO 11359-2
Deflection Temperature at 1.8 MPa (264 psi)	116 °C	241 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	121 °C	250 °F	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	138 °C	280 °F	Rate A/50; ASTM D1525
	138 °C	280 °F	Rate B/50; ISO 306
	139 °C	282 °F	Rate B/120; ISO 306
UL RTI, Electrical	130 °C	266 °F	UL 746B
UL RTI, Mechanical without Impact	130 °C	266 °F	UL 746B
Flammability, UL94	HB	HB	
	@Thickness 1.50 mm	@Thickness 0.0591 in	UL 94
Glow Wire Test	850 °C	1560 °F	IEC 60695-2-13
	850 °C	1560 °F	IEC 60695-2-13
	960 °C	1760 °F	
	@Thickness 3.00 mm	@Thickness 0.118 in	IEC 60695-2-12

Optical Properties	Metric	English	Comments
Haze	3.0 %	3.0 %	
	@Thickness 2.54 mm	@Thickness 0.100 in	ASTM D1003
Transmission, Visible	82 %	82 %	2.54 mm; ASTM D1003

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Volume Resistivity Electrical Properties	$\geq 1.00\text{e}+15$ ohm-cm Metric	$\geq 1.00\text{e}+15$ ohm-cm English	ASTM D257 Comments
Surface Resistance	$\geq 1.00\text{e}+15$ ohm	$\geq 1.00\text{e}+15$ ohm	ASTM D257

Descriptive Properties	Value	Comments
Ball Pressure Test, 125°C +/- 2°C	pass	IEC 60695-10-2

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China