

SABIC Innovative Plastics Lexan® EXL9330S PC Copolymer (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Opaque PC-Siloxane copolymer with excellent processability. UV stabilized. UL rated V-0/5VA/CTI-PLC-2. Available in limited colors.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-EXL9330S-PC-Copolymer-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	ASTM D792
Density	1.24 g/cc	0.0448 lb/in ³	ISO 1183
Moisture Absorption	0.0500 %	0.0500 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.12 %	0.12 %	ISO 62
Linear Mold Shrinkage, Flow	0.0040 - 0.0080 cm/cm @Thickness 3.20 mm	0.0040 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0040 - 0.0080 cm/cm @Thickness 3.20 mm	0.0040 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	8.0 g/10 min @Load 1.20 kg, Temperature 300 °C	8.0 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238
Melt Index of Compound	7.0 g/10 min @Load 1.20 kg, Temperature 300 °C	7.0 g/10 min @Load 2.65 lb, Temperature 572 °F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	58.0 MPa	8410 psi	50 mm/min; ISO 527
	58.0 MPa	8410 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	59.0 MPa	8560 psi	50 mm/min; ISO 527
	59.0 MPa	8560 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	100 %	100 %	50 mm/min; ISO 527
	100 %	100 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	6.0 %	6.0 %	50 mm/min; ISO 527
	6.0 %	6.0 %	Type I, 50 mm/min; ASTM D638

Tensile Modulus Mechanical Properties	2.15 GPa Metric	312 ksi English	1 mm/min; ISO 527 Comments
	2.15 GPa	312 ksi	50 mm/min; ASTM D638
Flexural Yield Strength	86.0 MPa	12500 psi	2 mm/min; ISO 178
	86.0 MPa	12500 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.15 GPa	312 ksi	2 mm/min; ISO 178
	2.15 GPa	312 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	7.00 J/cm	13.1 ft-lb/in	ASTM D256
	4.50 J/cm	8.43 ft-lb/in	ASTM D256
	@Temperature -50.0 °C	@Temperature -58.0 °F	
	5.50 J/cm	10.3 ft-lb/in	ASTM D256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Notched (ISO)	75.0 kJ/m ²	35.7 ft-lb/in ²	80*10*3; ISO 180/1A
	50.0 kJ/m ²	23.8 ft-lb/in ²	80*10*3; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Unnotched (ISO)	NB	NB	80*10*3; ISO 180/1U
	NB	NB	80*10*3; ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	7.00 J/cm ²	33.3 ft-lb/in ²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	5.00 J/cm ²	23.8 ft-lb/in ²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	139 °C	282 °F	Edgew 120*10*4 sp=100mm; ISO 75/Be
	139 °C	282 °F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa	126 °C	259 °F	

(264 psi) Thermal Properties	Metric	English	Flatw 80*10*4 sp=64mm; ISO 75/At Comments
	126 °C	259 °F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Vicat Softening Point	145 °C	293 °F	Rate B/50; ISO 306
	147 °C	297 °F	Rate B/120; ISO 306
	147 °C	297 °F	Rate B/50; ASTM D1525
UL RTI, Electrical	125 °C	257 °F	UL 746B
UL RTI, Mechanical with Impact	110 °C	230 °F	UL 746B
UL RTI, Mechanical without Impact	125 °C	257 °F	UL 746B
Flammability, UL94	V-0	V-0	UL 94
	@Thickness 0.800 mm	@Thickness 0.0315 in	
	5VB	5VB	UL 94
	@Thickness 2.00 mm	@Thickness 0.0787 in	
	5VA	5VA	UL 94
	@Thickness 2.50 mm	@Thickness 0.0984 in	
Glow Wire Test	900 °C	1650 °F	IEC 60695-2-13
	960 °C	1760 °F	IEC 60695-2-12
	@Thickness 0.800 - 3.00 mm	@Thickness 0.0315 - 0.118 in	

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	250 V	250 V	IEC 60112
	250 - 400 V	250 - 400 V	UL 746A
Hot Wire Ignition, HWI	30 - 60 sec	30 - 60 sec	UL 746A
High Amp Arc Ignition, HAI	>= 120 arcs	>= 120 arcs	UL 746A

Descriptive Properties	Value	Comments
Ball Pressure Test, 125°C +/- 2°C	PASSES	IEC 60695-10-2
UV-light, water exposure/immersion	F1	UL 746C

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China