

SABIC Innovative Plastics Lexan® EXRL0681 PC Copolymer

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

25 MFR LEXAN High Flow Ductile Copolymer This data was supplied by SABIC-IP for the Americas region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-EXRL0681-PC-Copolymer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D 792
Density	1.20 g/cc	0.0434 lb/in ³	ASTM D 792
	1.20 g/cc	0.0434 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.15 %	0.15 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.30 %	0.30 %	ISO 62
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	
Melt Flow	23 g/10 min	23 g/10 min	[cm ³ /10 min] Melt Volume Rate; ISO 1133
	@Load 1.20 kg, Temperature 300 °C	@Load 2.65 lb, Temperature 572 °F	
	25 g/10 min	25 g/10 min	ASTM D 1238
	@Load 1.20 kg, Temperature 300 °C	@Load 2.65 lb, Temperature 572 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D 785
Tensile Strength at Break	60.0 MPa	8700 psi	Type I, 50 mm/min; ASTM D 638
	65.0 MPa	9430 psi	50 mm/min; ISO 527
Tensile Strength, Yield	59.0 MPa	8560 psi	Type I, 50 mm/min; ASTM D 638
	62.0 MPa	8990 psi	50 mm/min; ISO 527
Elongation at Break	123 %	123 %	50 mm/min; ISO 527
	132 %	132 %	Type I, 50 mm/min; ASTM D 638
Elongation at Yield	6.0 %	6.0 %	Type I, 50 mm/min; ASTM D 638

Mechanical Properties	6.0% Metric	6.0% English	50 mm/min; ISO 527 Comments
Tensile Modulus	2.18 GPa	316 ksi	1 mm/min; ISO 527
	2.23 GPa	323 ksi	5 mm/min; ASTM D 638
Flexural Yield Strength	90.0 MPa	13100 psi	2 mm/min; ISO 178
	99.0 MPa	14400 psi	1.3 mm/min, 50 mm span; ASTM D 790
Flexural Modulus	2.18 GPa	316 ksi	2 mm/min; ISO 178
	2.22 GPa	322 ksi	1.3 mm/min, 50 mm span; ASTM D 790
Izod Impact, Notched	7.89 J/cm	14.8 ft-lb/in	ASTM D 256
	@Temperature 0.000 °C	@Temperature 32.0 °F	
	8.12 J/cm	15.2 ft-lb/in	ASTM D 256
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Izod Impact, Notched (ISO)	13.0 kJ/m ²	6.19 ft-lb/in ²	80*10*3; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	64.0 kJ/m ²	30.5 ft-lb/in ²	80*10*3; ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Izod Impact, Unnotched (ISO)	NB	NB	80*10*3; ISO 180/1U
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	NB	NB	80*10*3; ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	1.30 J/cm ²	6.19 ft-lb/in ²	V-notch Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	7.30 J/cm ²	34.7 ft-lb/in ²	V-notch Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Impact Test	110 J	81.1 ft-lb	Multiaxial Impact; ISO 6603
	67.0 J	49.4 ft-lb	Instrumented Impact Total Energy; ASTM D 3763

Mechanical Properties	@Temperature 23.0 °C Metric	@Temperature 73.4 °F English	Comments
Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	80.0 µm/m-°C	44.4 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	80.0 µm/m-°C	44.4 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
CTE, linear, Transverse to Flow	80.0 µm/m-°C	44.4 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	80.0 µm/m-°C	44.4 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
Deflection Temperature at 0.46 MPa (66 psi)	122 °C	252 °F	unannealed; ASTM D 648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	115 °C	239 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	111 °C	232 °F	
Vicat Softening Point	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D 648
	129 °C	264 °F	Rate B/50; ISO 306
	130 °C	266 °F	Rate B/120; ISO 306
	135 °C	275 °F	Rate B/50; ASTM D 1525

Optical Properties	Metric	English	Comments
Refractive Index	1.582	1.582	ASTM D 542
Haze	<= 1.0 %	<= 1.0 %	ASTM D 1003
	@Thickness 2.54 mm	@Thickness 0.100 in	
Transmission, Visible	88 %	88 %	ASTM D 1003
	@Thickness 2.54 mm	@Thickness 0.100 in	

Descriptive Properties	Value	Comments
Ball Pressure Test, 125°C +/- 2°C	PASS	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China