

SABIC Innovative Plastics Lexan® FXD101R PC (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Transparent/translucent PC for light diffusion special effects. Thicker sections without sinks. Internal mold release. Pigment package may affect properties. Application testing always recommended. This data was supplied by SABIC-IP for the Europe-Africa-Middle East region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-FXD101R-PC-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.15 %	0.15 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.35 % @Temperature 23.0 °C	0.35 % @Temperature 73.4 °F	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	on tensile bar; SABIC Method
Melt Flow	6.0 g/10 min @Load 1.20 kg, Temperature 300 °C	6.0 g/10 min @Load 2.65 lb, Temperature 572 °F	[cm ³ /10 min] Melt Volume Rate; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	70.0 MPa	10200 psi	50 mm/min; ISO 527
Tensile Strength, Yield	63.0 MPa	9140 psi	50 mm/min; ISO 527
Elongation at Break	120 %	120 %	50 mm/min; ISO 527
Elongation at Yield	6.0 %	6.0 %	50 mm/min; ISO 527
Tensile Modulus	2.35 GPa	341 ksi	1 mm/min; ISO 527
Flexural Yield Strength	90.0 MPa	13100 psi	2 mm/min; ISO 178
Flexural Modulus	2.30 GPa	334 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	12.0 kJ/m ² @Temperature -30.0 °C	5.71 ft-lb/in ² @Temperature -22.0 °F	80*10*3; ISO 180/1A
	70.0 kJ/m ² @Temperature 23.0 °C	33.3 ft-lb/in ² @Temperature 73.4 °F	80*10*3; ISO 180/1A
Izod Impact, Unnotched (ISO)	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	80*10*3; ISO 180/1U

Mechanical Properties	^{NB} Metric	^{NB} English	Comments
	@Temperature -30.0 °C	@Temperature -22.0 °F	ISO 180/1U
Charpy Impact Unnotched	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	NB @Temperature -30.0 °C	NB @Temperature -22.0 °F	Edgew 80*10*3 sp=62mm; ISO 179/1eU
Charpy Impact, Notched	1.50 J/cm ² @Temperature -30.0 °C	7.14 ft-lb/in ² @Temperature -22.0 °F	V-notch Edgew 80*10*3 sp=62mm; ISO 179/1eA
	3.50 J/cm ² @Temperature 23.0 °C	16.7 ft-lb/in ² @Temperature 73.4 °F	ISO 179/2C
	7.50 J/cm ² @Temperature 23.0 °C	35.7 ft-lb/in ² @Temperature 73.4 °F	V-notch Edgew 80*10*3 sp=62mm; ISO 179/1eA

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 µm/m-°C @Temperature 23.0 - 80.0 °C	38.9 µin/in-°F @Temperature 73.4 - 176 °F	ISO 11359-2
CTE, linear, Transverse to Flow	74.6 µm/m-°C @Temperature 23.0 - 80.0 °C	41.4 µin/in-°F @Temperature 73.4 - 176 °F	ISO 11359-2
Hot Ball Pressure Test	<= 140 °C	<= 284 °F	IEC 60695-10-2
Deflection Temperature at 0.46 MPa (66 psi)	138 °C	280 °F	Edgew 120*10*4 sp=100mm; ISO 75/Be
Deflection Temperature at 1.8 MPa (264 psi)	127 °C	261 °F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
Vicat Softening Point	144 °C	291 °F	Rate B/50; ISO 306
	145 °C	293 °F	Rate B/120; ISO 306
Flammability, UL94	HB @Thickness 0.700 mm	HB @Thickness 0.0276 in	UL 94
	HB @Thickness 3.00 mm	HB @Thickness 0.118 in	2nd value; UL 94
Oxygen Index	25 %	25 %	LOI; ISO 4589
Glow Wire Test	850 °C	1560 °F	Glow Wire Flammability Index; IEC

Thermal Properties	@Thickness 1.00 mm Metric	@Thickness 0.0394 in English	60695-2-12 Comments
Optical Properties	Metric	English	Comments
Refractive Index	1.586	1.586	ISO 489
Haze	<= 0.80 % @Thickness 2.54 mm	<= 0.80 % @Thickness 0.100 in	ASTM D 1003
Transmission, Visible	88 - 90 % @Thickness 2.54 mm	88 - 90 % @Thickness 0.100 in	ASTM D 1003
Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	ROA; IEC 60093
Dielectric Strength	17.0 kV/mm @Thickness 3.20 mm	432 kV/in @Thickness 0.126 in	in oil; IEC 60243-1
Descriptive Properties		Value	Comments
Ball Pressure Test, 125°C +/- 2°C		PASSES	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China