

SABIC Innovative Plastics Lexan® FXD1414T PC Copolymer (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

PC-siloxane copolymer in special light diffusion colors. Medium flow. Improved toughness compared to medium flow standard PC in same color. Color package may affect performance.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-FXD1414T-PC-Copolymer-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.18 g/cc	1.18 g/cc	ASTM D792
Density	1.18 g/cc	0.0426 lb/in ³	ISO 1183
Moisture Absorption	0.0900 %	0.0900 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.12 %	0.12 %	ISO 62
Linear Mold Shrinkage, Flow	0.0040 - 0.0080 cm/cm	0.0040 - 0.0080 in/in	on Tensile Bar; SABIC Method
	0.0040 - 0.0080 cm/cm @Thickness 3.20 mm	0.0040 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0040 - 0.0080 cm/cm @Thickness 3.20 mm	0.0040 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	10 g/10 min @Load 1.20 kg, Temperature 300 °C	10 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238
Melt Index of Compound	9.0 g/10 min @Load 1.20 kg, Temperature 300 °C	9.0 g/10 min @Load 2.65 lb, Temperature 572 °F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	51.0 MPa	7400 psi	Type I, 50 mm/min; ASTM D638
	54.0 MPa	7830 psi	50 mm/min; ISO 527
Tensile Strength, Yield	57.0 MPa	8270 psi	50 mm/min; ISO 527
	59.0 MPa	8560 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	84 %	84 %	Type I, 50 mm/min; ASTM D638
	107 %	107 %	50 mm/min; ISO 527
Elongation at Yield	5.4 %	5.4 %	50 mm/min; ISO 527

Mechanical Properties	Metric	English	Comments
			Type I, 50 mm/min; ASTM D638
Tensile Modulus	2.24 GPa	325 ksi	50 mm/min; ASTM D638
	2.30 GPa	334 ksi	1 mm/min; ISO 527
Flexural Yield Strength	85.0 MPa	12300 psi	1.3 mm/min, 50 mm span; ASTM D790
	89.0 MPa	12900 psi	2 mm/min; ISO 178
Flexural Modulus	2.15 GPa	312 ksi	2 mm/min; ISO 178
	2.22 GPa	322 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	8.17 J/cm	15.3 ft-lb/in	ASTM D256
	7.21 J/cm	13.5 ft-lb/in	ASTM D256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Notched (ISO)	65.0 kJ/m ²	30.9 ft-lb/in ²	80*10*3; ISO 180/1A
	55.0 kJ/m ²	26.2 ft-lb/in ²	80*10*3; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Unnotched (ISO)	NB	NB	80*10*3; ISO 180/1U
	NB	NB	80*10*3; ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	7.00 J/cm ²	33.3 ft-lb/in ²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	6.00 J/cm ²	28.6 ft-lb/in ²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Dart Drop, Total Energy	76.0 J	56.1 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	67.0 µm/m-°C	37.2 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 95.0 °C	@Temperature -40.0 - 203 °F	

Thermal Properties	Metric $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	English $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	Comments
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	ISO 11359-2
CTE, linear, Transverse to Flow	80.0 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	44.4 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	ASTM E 831
	@Temperature -40.0 - 95.0 °C	@Temperature -40.0 - 203 °F	
	80.0 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	44.4 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	ISO 11359-2
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	
Deflection Temperature at 1.8 MPa (264 psi)	116 °C	241 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	122 °C	252 °F	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	138 °C	280 °F	Rate B/50; ASTM D1525
	138 °C	280 °F	Rate B/50; ISO 306
	142 °C	288 °F	Rate B/120; ISO 306

Descriptive Properties	Value	Comments
Ball Pressure Test, 125°C +/- 2°C	pass	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China