

SABIC Innovative Plastics Lexan® FXR123R PC (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Lexan FXR123R Resin

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-FXR123R-PC-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.33 g/cc	0.0480 lb/in ³	ISO 1183
Moisture Absorption	0.150 %	0.150 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.35 %	0.35 %	ISO 62
Melt Index of Compound	21 g/10 min @Load 1.20 kg, Temperature 300 °C	21 g/10 min @Load 2.65 lb, Temperature 572 °F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	50.0 MPa	7250 psi	50 mm/min; ISO 527
Tensile Strength, Yield	60.0 MPa	8700 psi	50 mm/min; ISO 527
Elongation at Break	60 %	60 %	50 mm/min; ISO 527
Elongation at Yield	6.0 %	6.0 %	50 mm/min; ISO 527
Tensile Modulus	2.50 GPa	363 ksi	1 mm/min; ISO 527
Flexural Yield Strength	90.0 MPa	13100 psi	2 mm/min; ISO 178
Flexural Modulus	2.40 GPa	348 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	60.0 kJ/m ²	28.6 ft-lb/in ²	80*10*3; ISO 180/1A
	10.0 kJ/m ² @Temperature -30.0 °C	4.76 ft-lb/in ² @Temperature -22.0 °F	80*10*3; ISO 180/1A
Izod Impact, Unnotched (ISO)	NB	NB	80*10*3; ISO 180/1U
	NB @Temperature -30.0 °C	NB @Temperature -22.0 °F	80*10*3; ISO 180/1U
Charpy Impact Unnotched	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	NB	NB	Edgew 80*10*3 sp=62mm; ISO

Mechanical Properties	@Temperature -30.0 °C Metric	@Temperature -22.0 °F English	179/1eA Comments
Charpy Impact, Notched	6.00 J/cm ²	28.6 ft-lb/in ²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	1.00 J/cm ²	4.76 ft-lb/in ²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Transverse to Flow	60.0 µm/m-°C	33.3 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
Vicat Softening Point	140 °C	284 °F	Rate B/50; ISO 306
	141 °C	286 °F	Rate B/120; ISO 306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China