

## SABIC Innovative Plastics Lexan® HF1110R PC

Category : Polymer , Thermoplastic , Polycarbonate (PC)

### Material Notes:

High flow grade. Easy mold release version of LEXAN HF1110. For thin wall lighting lenses, data storage components and safety eyewear lenses.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-Lexan-HF1110R-PC.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-HF1110R-PC.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	25 g/10 min @Load 1.20 kg, Temperature 300 °C	25 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	65.0 MPa	9430 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	62.0 MPa	8990 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	120 %	120 %	Type I, 50 mm/min; ASTM D638
Flexural Yield Strength	93.0 MPa	13500 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.30 GPa	334 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	6.40 J/cm	12.0 ft-lb/in	ASTM D256
Tensile Impact Strength	378 kJ/m <sup>2</sup>	180 ft-lb/in <sup>2</sup>	Type S; ASTM D1822
Dart Drop, Total Energy	54.0 J	39.8 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	126 °C @Thickness 3.20 mm	259 °F @Thickness 0.126 in	unannealed; ASTM D648
UL RTI, Electrical	130 °C	266 °F	UL 746B
UL RTI, Mechanical with Impact	130 °C	266 °F	UL 746B
UL RTI, Mechanical without Impact	130 °C	266 °F	UL 746B

Thermal Properties	Metric	English	Comments
Flammability, UL94	@Thickness 1.09 mm	@Thickness 0.0429 in	UL 94

Optical Properties	Metric	English	Comments
Haze	1.0 % @Thickness 2.54 mm	1.0 % @Thickness 0.100 in	ASTM D1003
Transmission, Visible	88 %	88 %	2.54 mm; ASTM D1003

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	250 - 400 V	250 - 400 V	UL 746A
Hot Wire Ignition, HWI	30 - 60 sec	30 - 60 sec	UL 746A
High Amp Arc Ignition, HAI	60 - 120 arcs	60 - 120 arcs	UL 746A
High Voltage Arc-Tracking Rate, HVTR	25.4 - 80.0 mm/min	1.00 - 3.15 in/min	UL 746A

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China