

**SABIC Innovative Plastics Lexan® HFD1034 PC Copolymer (Asia Pacific)**

Category : Polymer , Thermoplastic , Polycarbonate (PC)

**Material Notes:**

7 MFR LEXAN HFD Copolymer UV-stabilized, available in transparent colors only

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-Lexan-HFD1034-PC-Copolymer-Asia-Pacific.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-HFD1034-PC-Copolymer-Asia-Pacific.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Density	1.20 g/cc	0.0434 lb/in <sup>3</sup>	ASTM D792
	1.20 g/cc	0.0434 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption	0.150 %	0.150 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.30 %	0.30 %	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	7.0 g/10 min @Load 1.20 kg, Temperature 300 °C	7.0 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238
Melt Index of Compound	6.0 g/10 min @Load 1.20 kg, Temperature 300 °C	6.0 g/10 min @Load 2.65 lb, Temperature 572 °F	MVR [cm <sup>3</sup> /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength at Break	67.0 MPa	9720 psi	Type I, 50 mm/min; ASTM D638
	73.0 MPa	10600 psi	50 mm/min; ISO 527
Tensile Strength, Yield	58.0 MPa	8410 psi	Type I, 50 mm/min; ASTM D638
	60.0 MPa	8700 psi	50 mm/min; ISO 527
Elongation at Break	141 %	141 %	50 mm/min; ISO 527
	142 %	142 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	6.0 %	6.0 %	Type I, 50 mm/min; ASTM D638
	6.0 %	6.0 %	50 mm/min; ISO 527

Mechanical Properties	Metric	English	Comments
	2.26 GPa	328 ksi	5 mm/min; ASTM D638
Flexural Yield Strength	89.0 MPa	12900 psi	2 mm/min; ISO 178
	98.0 MPa	14200 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.07 GPa	300 ksi	2 mm/min; ISO 178
	2.24 GPa	325 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	9.66 J/cm	18.1 ft-lb/in	ASTM D256
	8.99 J/cm	16.8 ft-lb/in	ASTM D256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Notched (ISO)	72.0 kJ/m <sup>2</sup>	34.3 ft-lb/in <sup>2</sup>	80*10*3; ISO 180/1A
	63.0 kJ/m <sup>2</sup>	30.0 ft-lb/in <sup>2</sup>	80*10*3; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Unnotched (ISO)	NB	NB	80*10*3; ISO 180/1U
	NB	NB	80*10*3; ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	8.20 J/cm <sup>2</sup>	39.0 ft-lb/in <sup>2</sup>	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	6.90 J/cm <sup>2</sup>	32.8 ft-lb/in <sup>2</sup>	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Dart Drop, Total Energy	78.0 J	57.5 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Impact Test	134 J	98.8 ft-lb	Multiaxial Impact; ISO 6603

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	80.0 µm/m-°C	44.4 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	

Thermal Properties	80.0 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$ Metric	44.4 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$ English	Comments ISO 11359-2
	@Temperature -40.0 - 40.0 $^\circ\text{C}$	@Temperature -40.0 - 104 $^\circ\text{F}$	
CTE, linear, Transverse to Flow	80.0 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	44.4 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	ASTM E 831
	@Temperature -40.0 - 40.0 $^\circ\text{C}$	@Temperature -40.0 - 104 $^\circ\text{F}$	
	80.0 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	44.4 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	ISO 11359-2
	@Temperature -40.0 - 40.0 $^\circ\text{C}$	@Temperature -40.0 - 104 $^\circ\text{F}$	
Deflection Temperature at 0.46 MPa (66 psi)	125 $^\circ\text{C}$	257 $^\circ\text{F}$	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	115 $^\circ\text{C}$	239 $^\circ\text{F}$	Flatw 80*10*4 sp=64mm; ISO 75/Af
	115 $^\circ\text{C}$	239 $^\circ\text{F}$	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	130 $^\circ\text{C}$	266 $^\circ\text{F}$	Rate B/50; ISO 306
	131 $^\circ\text{C}$	268 $^\circ\text{F}$	Rate B/120; ISO 306
	136 $^\circ\text{C}$	277 $^\circ\text{F}$	Rate B/50; ASTM D1525

Optical Properties	Metric	English	Comments
Refractive Index	1.582	1.582	ASTM D542
Haze	$\leq 1.0 \%$	$\leq 1.0 \%$	ASTM D1003
	@Thickness 2.54 mm	@Thickness 0.100 in	
Transmission, Visible	88 %	88 %	2.54 mm; ASTM D1003

Descriptive Properties	Value	Comments
Ball Pressure Test, 125 $^\circ\text{C}$ +/- 2 $^\circ\text{C}$	PASS	IEC 60695-10-2

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China