

## SABIC Innovative Plastics Lexan® HFD1433 PC Copolymer (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

### Material Notes:

11 MFR LEXAN High Flow Ductile Copolymer UV stabilized, available in transparent colors only

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-Lexan-HFD1433-PC-Copolymer-Europe-Africa-Middle-East.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-HFD1433-PC-Copolymer-Europe-Africa-Middle-East.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Density	1.20 g/cc	0.0434 lb/in <sup>3</sup>	ASTM D792
	1.20 g/cc	0.0434 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption	0.150 %	0.150 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.30 %	0.30 %	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	
Melt Flow	11 g/10 min	11 g/10 min	ASTM D1238
	@Load 1.20 kg, Temperature 300 °C	@Load 2.65 lb, Temperature 572 °F	
Melt Index of Compound	10 g/10 min	10 g/10 min	MVR [cm <sup>3</sup> /10 min]; ISO 1133
	@Load 1.20 kg, Temperature 300 °C	@Load 2.65 lb, Temperature 572 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength at Break	67.0 MPa	9720 psi	Type I, 50 mm/min; ASTM D638
	68.0 MPa	9860 psi	50 mm/min; ISO 527
Tensile Strength, Yield	58.0 MPa	8410 psi	Type I, 50 mm/min; ASTM D638
	61.0 MPa	8850 psi	50 mm/min; ISO 527
Elongation at Break	126 %	126 %	50 mm/min; ISO 527
	137 %	137 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	6.0 %	6.0 %	50 mm/min; ISO 527

Mechanical Properties	6.0% Metric	6.0% English	Type I, 50 mm/min; ASTM D638 Comments
Tensile Modulus	2.12 GPa	307 ksi	1 mm/min; ISO 527
	2.24 GPa	325 ksi	5 mm/min; ASTM D638
Flexural Yield Strength	90.0 MPa	13100 psi	2 mm/min; ISO 178
	98.0 MPa	14200 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.09 GPa	303 ksi	2 mm/min; ISO 178
	2.23 GPa	323 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	9.03 J/cm	16.9 ft-lb/in	ASTM D256
	4.35 J/cm	8.15 ft-lb/in	ASTM D256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Notched	8.59 J/cm	16.1 ft-lb/in	ASTM D256
	@Temperature -20.0 °C	@Temperature -4.00 °F	
Izod Impact, Notched (ISO)	70.0 kJ/m <sup>2</sup>	33.3 ft-lb/in <sup>2</sup>	80*10*3; ISO 180/1A
	32.0 kJ/m <sup>2</sup>	15.2 ft-lb/in <sup>2</sup>	80*10*3; ISO 180/1A
Izod Impact, Notched (ISO)	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Unnotched (ISO)	NB	NB	80*10*3; ISO 180/1U
	NB	NB	80*10*3; ISO 180/1U
Izod Impact, Unnotched (ISO)	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
Charpy Impact Unnotched	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	8.00 J/cm <sup>2</sup>	38.1 ft-lb/in <sup>2</sup>	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	4.30 J/cm <sup>2</sup>	20.5 ft-lb/in <sup>2</sup>	Edgew 80*10*3 sp=62mm; ISO 179/1eA
Charpy Impact, Notched	@Temperature -30.0 °C	@Temperature -22.0 °F	
Dart Drop, Total Energy	77.0 J	56.8 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Dart Drop, Total Energy			
Impact Test	120 J	88.5 ft-lb	Multiaxial Impact; ISO 6603

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	80.0 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	44.4 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	ASTM E 831
	@Temperature -40.0 - 40.0 $^\circ\text{C}$	@Temperature -40.0 - 104 $^\circ\text{F}$	
	80.0 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	44.4 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	ISO 11359-2
	@Temperature -40.0 - 40.0 $^\circ\text{C}$	@Temperature -40.0 - 104 $^\circ\text{F}$	
CTE, linear, Transverse to Flow	80.0 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	44.4 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	ASTM E 831
	@Temperature -40.0 - 40.0 $^\circ\text{C}$	@Temperature -40.0 - 104 $^\circ\text{F}$	
	80.0 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	44.4 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	ISO 11359-2
	@Temperature -40.0 - 40.0 $^\circ\text{C}$	@Temperature -40.0 - 104 $^\circ\text{F}$	
Deflection Temperature at 0.46 MPa (66 psi)	124 $^\circ\text{C}$	255 $^\circ\text{F}$	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	115 $^\circ\text{C}$	239 $^\circ\text{F}$	Flatw 80*10*4 sp=64mm; ISO 75/Af
	114 $^\circ\text{C}$	237 $^\circ\text{F}$	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	130 $^\circ\text{C}$	266 $^\circ\text{F}$	Rate B/50; ISO 306
	131 $^\circ\text{C}$	268 $^\circ\text{F}$	Rate B/120; ISO 306
	136 $^\circ\text{C}$	277 $^\circ\text{F}$	Rate B/50; ASTM D1525

Optical Properties	Metric	English	Comments
Refractive Index	1.582	1.582	ASTM D542
Haze	$\leq 1.0\%$	$\leq 1.0\%$	ASTM D1003
	@Thickness 2.54 mm	@Thickness 0.100 in	
Transmission, Visible	88 %	88 %	2.54 mm; ASTM D1003

Descriptive Properties	Value	Comments
Ball Pressure Test, 125 $^\circ\text{C}$ +/- 2 $^\circ\text{C}$	PASS	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China