

SABIC Innovative Plastics Lexan® HP2NR PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Med/high flow polycarbonate. For medical devices and pharmaceutical applications. Healthcare management of change, biocompatible (ISO10993 or USP Class VI). EtO and steam sterilizable. Contains no mold release.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-HP2NR-PC-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Density	1.19 g/cc	0.0430 lb/in ³	ASTM D792
	1.19 g/cc	0.0430 lb/in ³	ISO 1183
Water Absorption	0.15 % @Time 86400 sec	0.15 % @Time 24.0 hour	ASTM D570
Moisture Absorption	0.150 %	0.150 %	23°C / 50% RH; ISO 62
Moisture Absorption at Equilibrium	0.35 %	0.35 %	ASTM D570
	0.58 % @Temperature 100 °C	0.58 % @Temperature 212 °F	ASTM D570
Water Absorption at Saturation	0.35 %	0.35 %	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	17.5 g/10 min @Load 1.20 kg, Temperature 300 °C	17.5 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238
Melt Index of Compound	16 g/10 min @Load 1.20 kg, Temperature 300 °C	16 g/10 min @Load 2.65 lb, Temperature 572 °F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	70	70	ASTM D785
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength at Break	65.0 MPa	9430 psi	50 mm/min; ISO 527
	68.0 MPa	9860 psi	Type I, 50 mm/min; ASTM D638

Mechanical Properties	Metric	English	Comments
	63.0 MPa	9140 psi	50 mm/min; ISO 527
Elongation at Break	100 %	100 %	50 mm/min; ISO 527
	125 %	125 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	6.0 %	6.0 %	50 mm/min; ISO 527
	7.0 %	7.0 %	Type I, 50 mm/min; ASTM D638
Tensile Modulus	2.35 GPa	341 ksi	1 mm/min; ISO 527
	2.37 GPa	344 ksi	50 mm/min; ASTM D638
Flexural Yield Strength	90.0 MPa	13100 psi	2 mm/min; ISO 178
	96.0 MPa	13900 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.30 GPa	334 ksi	2 mm/min; ISO 178
	2.34 GPa	339 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	6.94 J/cm	13.0 ft-lb/in	ASTM D256
Izod Impact, Unnotched	32.04 J/cm	60.02 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	60.0 kJ/m ²	28.6 ft-lb/in ²	80*10*3; ISO 180/1A
	10.0 kJ/m ²	4.76 ft-lb/in ²	80*10*3; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Unnotched (ISO)	NB	NB	80*10*3; ISO 180/1U
	NB	NB	80*10*3; ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	3.50 J/cm ²	16.7 ft-lb/in ²	ISO 179/2C
	6.50 J/cm ²	30.9 ft-lb/in ²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	1.00 J/cm ²	4.76 ft-lb/in ²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Tensile Impact Strength Mechanical Properties	546 kJ/m ² Metric	260 ft-lb/in ² English	Type S- ASTM D1822 Comments
Dart Drop, Total Energy	169 J	125 ft-lb	ASTM D3029
	62.0 J @Temperature 23.0 °C	45.7 ft-lb @Temperature 73.4 °F	ASTM D3763
Taber Abrasion, mg/1000 Cycles	10	10	CS-17, 1 kg; ASTM D1044

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	68.4 µm/m-°C	38.0 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 95.0 °C	@Temperature -40.0 - 203 °F	
	70.0 µm/m-°C	38.9 µin/in-°F	ISO 11359-2
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	
CTE, linear, Transverse to Flow	68.4 µm/m-°C	38.0 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 95.0 °C	@Temperature -40.0 - 203 °F	
	70.0 µm/m-°C	38.9 µin/in-°F	ISO 11359-2
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	
Specific Heat Capacity	1.25 J/g-°C	0.299 BTU/lb-°F	ASTM C351
Thermal Conductivity	0.190 W/m-K	1.32 BTU-in/hr-ft ² -°F	ASTM C177
	0.200 W/m-K	1.39 BTU-in/hr-ft ² -°F	ISO 8302
Deflection Temperature at 0.46 MPa (66 psi)	137 °C	279 °F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Deflection Temperature at 1.8 MPa (264 psi)	122 °C	252 °F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
	129 °C	264 °F	
	@Thickness 6.40 mm	@Thickness 0.252 in	unannealed; ASTM D648
Vicat Softening Point	140 °C	284 °F	Rate B/50; ISO 306
	141 °C	286 °F	Rate B/120; ISO 306
	154 °C	309 °F	Rate B/50; ASTM D1525
UL RTI, Electrical	130 °C	266 °F	UL 746B

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	IEC 60093
	>= 1.00e+17 ohm-cm	>= 1.00e+17 ohm-cm	ASTM D257
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	ROA; IEC 60093
Dielectric Constant	2.7	2.7	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	2.7	2.7	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
	2.96	2.96	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	3.17	3.17	ASTM D150
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Dielectric Strength	14.9 kV/mm	378 kV/in	in air; ASTM D149
	@Thickness 3.20 mm	@Thickness 0.126 in	
	17.0 kV/mm	432 kV/in	in oil; IEC 60243-1
	@Thickness 3.20 mm	@Thickness 0.126 in	
Dissipation Factor	0.00090	0.00090	ASTM D150
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
	0.0010	0.0010	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
	0.010	0.010	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	0.010	0.010	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	250 - 400 V	250 - 400 V	UL 746A
Hot Wire Ignition, HWI	30 - 60 sec	30 - 60 sec	UL 746A
High Amp Arc Ignition, HAI	60 - 120 arcs	60 - 120 arcs	UL 746A

Electrical Properties	Metric	English	Comments
High Voltage Arc-Tracking Rate, HVTR	23.4 - 80.0 mm ³ /min	1.00 - 3.15 in ³ /min	UL 746A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China