

SABIC Innovative Plastics Lexan® HP4 PC

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Medium flow polycarbonate. For medical devices and pharmaceutical applications. Healthcare management of change, biocompatible (ISO10993 or USP Class VI). EtO and steam sterilizable. Contains mold release.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-HP4-PC.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Density	1.19 g/cc	0.0430 lb/in ³	ASTM D792
Water Absorption	0.15 % @Time 86400 sec	0.15 % @Time 24.0 hour	ASTM D570
Moisture Absorption at Equilibrium	0.35 %	0.35 %	ASTM D570
	0.58 % @Temperature 100 °C	0.58 % @Temperature 212 °F	ASTM D570
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	10.5 g/10 min @Load 1.20 kg, Temperature 300 °C	10.5 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238
Melt Index of Compound	10 g/10 min @Load 1.20 kg, Temperature 300 °C	10 g/10 min @Load 2.65 lb, Temperature 572 °F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	70	70	ASTM D785
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength at Break	68.0 MPa	9860 psi	Type I, 50 mm/min; ASTM D638
	70.0 MPa	10200 psi	50 mm/min; ISO 527
Tensile Strength, Yield	62.0 MPa	8990 psi	Type I, 50 mm/min; ASTM D638
	63.0 MPa	9140 psi	50 mm/min; ISO 527
Elongation at Break	110 %	110 %	50 mm/min; ISO 527

Mechanical Properties	Metric	English	Comments
Elongation at Yield	6.0 %	6.0 %	50 mm/min; ISO 527
	7.0 %	7.0 %	Type I, 50 mm/min; ASTM D638
Tensile Modulus	2.35 GPa	341 ksi	1 mm/min; ISO 527
	2.37 GPa	344 ksi	50 mm/min; ASTM D638
Flexural Yield Strength	90.0 MPa	13100 psi	2 mm/min; ISO 178
	97.0 MPa	14100 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.30 GPa	334 ksi	2 mm/min; ISO 178
	2.34 GPa	339 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	8.01 J/cm	15.0 ft-lb/in	colors; ASTM D256
	8.01 J/cm	15.0 ft-lb/in	natural, tints; ASTM D256
	8.01 J/cm	15.0 ft-lb/in	ASTM D256
Izod Impact, Unnotched	32.04 J/cm	60.02 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	12.0 kJ/m ²	5.71 ft-lb/in ²	80*10*4; ISO 180/1A
	10.0 kJ/m ² @Temperature -30.0 °C	4.76 ft-lb/in ² @Temperature -22.0 °F	80*10*4; ISO 180/1A
Charpy Impact, Notched	3.50 J/cm ²	16.7 ft-lb/in ²	ISO 179/2C
Tensile Impact Strength	577 kJ/m ²	275 ft-lb/in ²	Type S; ASTM D1822
Dart Drop, Total Energy	63.0 J	46.5 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763
	169 J	125 ft-lb	ASTM D3029
Taber Abrasion, mg/1000 Cycles	10	10	CS-17, 1 kg; ASTM D1044

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	68.4 µm/m-°C	38.0 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 95.0 °C	@Temperature -40.0 - 203 °F	
	70.0 µm/m-°C	38.9 µin/in-°F	ISO 11359-2
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.190 W/m-K	1.32 BTU-in/hr-ft ² -°F	ASTM C177
	0.200 W/m-K	1.39 BTU-in/hr-ft ² -°F	ISO 8302
Deflection Temperature at 0.46 MPa (66 psi)	136 °C	277 °F	Edgew 120*10*4 sp=100mm; ISO 75/Be
	137 °C @Thickness 6.40 mm	279 °F @Thickness 0.252 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	125 °C	257 °F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
	132 °C @Thickness 6.40 mm	270 °F @Thickness 0.252 in	unannealed; ASTM D648
Vicat Softening Point	141 °C	286 °F	Rate B/50; ISO 306
	142 °C	288 °F	Rate B/120; ISO 306
	153 °C	307 °F	Rate A/50; ISO 306
	154 °C	309 °F	Rate B/50; ASTM D1525
UL RTI, Electrical	130 °C	266 °F	UL 746B
UL RTI, Mechanical with Impact	130 °C	266 °F	UL 746B
UL RTI, Mechanical without Impact	130 °C	266 °F	UL 746B
Flammability, UL94	HB @Thickness 1.47 mm	HB @Thickness 0.0579 in	UL 94
Oxygen Index	25 %	25 %	ASTM D2863
	25 %	25 %	ISO 4589

Optical Properties	Metric	English	Comments
Refractive Index	1.586	1.586	ASTM D542
Haze	1.0 % @Thickness 2.54 mm	1.0 % @Thickness 0.100 in	ASTM D1003
Transmission, Visible	88 %	88 %	2.54 mm; ASTM D1003

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	IEC 60093

Electrical Properties	$\geq 1.00\text{e}+17$ ohm-cm Metric	$\geq 1.00\text{e}+17$ ohm-cm English	ASTM D257 Comments
Surface Resistance	$\geq 1.00\text{e}+15$ ohm	$\geq 1.00\text{e}+15$ ohm	ROA; IEC 60093
Dielectric Constant	2.7	2.7	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	2.7	2.7	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
	2.96	2.96	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	3.17	3.17	ASTM D150
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Dielectric Strength	14.9 kV/mm	378 kV/in	in air; ASTM D149
	@Thickness 3.20 mm	@Thickness 0.126 in	
	17.0 kV/mm	432 kV/in	in oil; IEC 60243-1
	@Thickness 3.20 mm	@Thickness 0.126 in	
Dissipation Factor	0.00090	0.00090	ASTM D150
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
	0.0010	0.0010	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
	0.010	0.010	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	0.010	0.010	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	250 - 400 V	250 - 400 V	UL 746A
Hot Wire Ignition, HWI	30 - 60 sec	30 - 60 sec	UL 746A
High Amp Arc Ignition, HAI	60 - 120 arcs	60 - 120 arcs	UL 746A
High Voltage Arc-Tracking Rate, HVTR	25.4 - 80.0 mm/min	1.00 - 3.15 in/min	UL 746A

Descriptive Properties	Value	Comments
Ball Pressure Test, 125°C +/- 2°C	PASSES	IEC 60695-10-2
Specific Volume	0.83cm ³ /g	ASTM D792

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China