

## SABIC Innovative Plastics Lexan® HP6 PC

Category : Polymer , Thermoplastic , Polycarbonate (PC)

### Material Notes:

Low/med flow polycarbonate. For medical devices and pharmaceutical applications. Healthcare management of change, biocompatible (ISO10993 or USP Class VI). EtO and steam sterilizable. Contains mold release.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-Lexan-HP6-PC.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-HP6-PC.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Density	1.19 g/cc	0.0430 lb/in <sup>3</sup>	ASTM D792
	1.20 g/cc	0.0434 lb/in <sup>3</sup>	ISO 1183
Water Absorption	0.15 % @Time 86400 sec	0.15 % @Time 24.0 hour	ASTM D570
Moisture Absorption	0.150 %	0.150 %	23°C / 50% RH; ISO 62
Moisture Absorption at Equilibrium	0.35 %	0.35 %	ASTM D570
	0.58 % @Temperature 100 °C	0.58 % @Temperature 212 °F	ASTM D570
Water Absorption at Saturation	0.35 %	0.35 %	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	7.0 g/10 min @Load 1.20 kg, Temperature 300 °C	7.0 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238
Melt Index of Compound	4.0 g/10 min @Load 5.00 kg, Temperature 220 °C	4.0 g/10 min @Load 11.0 lb, Temperature 428 °F	MVR [cm <sup>3</sup> /10 min]; ISO 1133
	6.0 g/10 min @Load 1.20 kg, Temperature 300 °C	6.0 g/10 min @Load 2.65 lb, Temperature 572 °F	MVR [cm <sup>3</sup> /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	70	70	ASTM D785
Hardness, Rockwell R	118	118	ASTM D785

Mechanical Properties <small>Hardness, H350/3l</small>	Metric <small>98.0 MPa</small>	English <small>14200 psi</small>	Comments <small>ISO 2039-1</small>
Tensile Strength at Break	68.0 MPa	9860 psi	Type I, 50 mm/min; ASTM D638
	70.0 MPa	10200 psi	50 mm/min; ISO 527
Tensile Strength, Yield	62.0 MPa	8990 psi	Type I, 50 mm/min; ASTM D638
	63.0 MPa	9140 psi	50 mm/min; ISO 527
Elongation at Break	120 %	120 %	50 mm/min; ISO 527
	135 %	135 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	6.0 %	6.0 %	50 mm/min; ISO 527
	7.0 %	7.0 %	Type I, 50 mm/min; ASTM D638
Tensile Modulus	2.31 GPa	335 ksi	5 mm/min; ASTM D638
	2.35 GPa	341 ksi	1 mm/min; ISO 527
Flexural Yield Strength	90.0 MPa	13100 psi	2 mm/min; ISO 178
	97.0 MPa	14100 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.30 GPa	334 ksi	2 mm/min; ISO 178
	2.34 GPa	339 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	9.07 J/cm	17.0 ft-lb/in	ASTM D256
	1.39 J/cm	2.60 ft-lb/in	ASTM D256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Unnotched	32.04 J/cm	60.02 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	65.0 kJ/m <sup>2</sup>	30.9 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A
	10.0 kJ/m <sup>2</sup>	4.76 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	3.50 J/cm <sup>2</sup>	16.7 ft-lb/in <sup>2</sup>	ISO 179/2C
	9.50 J/cm <sup>2</sup>	45.2 ft-lb/in <sup>2</sup>	Edgew 80*10*4 sp=62mm; ISO 179/1eA
Tensile Impact Strength	630 kJ/m <sup>2</sup>	300 ft-lb/in <sup>2</sup>	Type S; ASTM D1822
Dart Drop, Total Energy	169 J	125 ft-lb	ASTM D3029
	65.0 J	47.9 ft-lb	

Mechanical Properties	Metric @ Temperature 23.0 °C	English @ Temperature 73.4 °F	ASTM D3763 Comments
Taber Abrasion, mg/1000 Cycles	10	10	CS-17, 1 kg; SABIC Method
	10	10	CS-17, 1 kg; ASTM D1044

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	60.0 µm/m-°C	33.3 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	62.0 µm/m-°C	34.4 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	70.0 µm/m-°C	38.9 µin/in-°F	ISO 11359-2
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	
CTE, linear, Transverse to Flow	57.0 µm/m-°C	31.7 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	60.0 µm/m-°C	33.3 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
Specific Heat Capacity	1.25 J/g-°C	0.299 BTU/lb-°F	ASTM C351
Thermal Conductivity	0.190 W/m-K	1.32 BTU-in/hr-ft <sup>2</sup> -°F	ASTM C177
	0.200 W/m-K	1.39 BTU-in/hr-ft <sup>2</sup> -°F	ISO 8302
Hot Ball Pressure Test	<= 140 °C	<= 284 °F	IEC 60695-10-2
Deflection Temperature at 0.46 MPa (66 psi)	138 °C	280 °F	Edgew 120*10*4 sp=100mm; ISO 75/Be
	137 °C	279 °F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Deflection Temperature at 1.8 MPa (264 psi)	124 °C	255 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	127 °C	261 °F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
	132 °C	270 °F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Vicat Softening Point	144 °C	291 °F	Rate B/50; ISO 306

Thermal Properties	Metric	English	Comments, ISO 306
<b>Electrical Properties</b>	<b>Metric</b>	<b>English</b>	<b>Comments</b>
Volume Resistivity	>= 1.00e+17 ohm-cm	>= 1.00e+17 ohm-cm	ASTM D257
Dielectric Constant	2.7	2.7	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	2.7	2.7	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
	2.96	2.96	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	3.17	3.17	ASTM D150
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Dielectric Strength	14.9 kV/mm	378 kV/in	in air; ASTM D149
	@Thickness 3.20 mm	@Thickness 0.126 in	
	17.0 kV/mm	432 kV/in	in oil; IEC 60243-1
	@Thickness 3.20 mm	@Thickness 0.126 in	
Dissipation Factor	0.00090	0.00090	ASTM D150
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
	0.0010	0.0010	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
	0.010	0.010	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	0.010	0.010	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	250 - 400 V	250 - 400 V	UL 746A
Hot Wire Ignition, HWI	30 - 60 sec	30 - 60 sec	UL 746A
High Amp Arc Ignition, HAI	60 - 120 arcs	60 - 120 arcs	UL 746A

High Voltage Arc-Tracking Rate,  
Electrical Properties

Metric 60.0 mm/min

English 2.36 in/min

Comments

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China