

## SABIC Innovative Plastics Lexan® HPH4504 PPC (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polyphthalate Carbonate

### Material Notes:

High heat specialty polycarbonate. For medical devices and pharmaceutical applications. Healthcare management of change, biocompatible (ISO10993 of USP Class VI). EtO, steam, gamma and e-beam sterilizable.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-Lexan-HPH4504-PPC-Europe-Africa-Middle-East.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-HPH4504-PPC-Europe-Africa-Middle-East.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Density	1.19 g/cc	0.0430 lb/in <sup>3</sup>	ASTM D792
	1.20 g/cc	0.0434 lb/in <sup>3</sup>	ISO 1183
Water Absorption	0.16 %	0.16 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Moisture Absorption	0.350 %	0.350 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.16 %	0.16 %	ISO 62
Linear Mold Shrinkage, Flow	0.0070 - 0.0080 cm/cm	0.0070 - 0.0080 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	
Melt Flow	3.0 g/10 min	3.0 g/10 min	ASTM D1238
	@Load 1.20 kg, Temperature 300 °C	@Load 2.65 lb, Temperature 572 °F	
Melt Index of Compound	3.0 g/10 min	3.0 g/10 min	MVR [cm <sup>3</sup> /10 min]; ISO 1133
	@Load 1.20 kg, Temperature 300 °C	@Load 2.65 lb, Temperature 572 °F	
	12 g/10 min	12 g/10 min	MVR [cm <sup>3</sup> /10 min]; ISO 1133
	@Load 2.16 kg, Temperature 330 °C	@Load 4.76 lb, Temperature 626 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	85	85	ASTM D785
Hardness, Rockwell R	122	122	ASTM D785
Tensile Strength at Break	65.0 MPa	9430 psi	50 mm/min; ISO 527
	71.0 MPa	10300 psi	Type I, 50 mm/min; ASTM D638

Tensile Strength, Yield Mechanical Properties	65.0 MPa Metric	9430 psi English	Type I, 50 mm/min; ASTM D638 Comments
	65.0 MPa	9430 psi	50 mm/min; ISO 527
Elongation at Break	7.0 %	7.0 %	50 mm/min; ISO 527
	122 %	122 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	7.0 %	7.0 %	Type I, 50 mm/min; ASTM D638
	7.0 %	7.0 %	50 mm/min; ISO 527
Tensile Modulus	2.09 GPa	303 ksi	5 mm/min; ASTM D638
	2.26 GPa	328 ksi	1 mm/min; ISO 527
Flexural Yield Strength	66.0 MPa	9570 psi	2 mm/min; ISO 178
	95.0 MPa	13800 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.02 GPa	293 ksi	1.3 mm/min, 50 mm span; ASTM D790
	2.12 GPa	307 ksi	2 mm/min; ISO 178
Izod Impact, Notched	6.40 J/cm	12.0 ft-lb/in	ASTM D256
	1.44 J/cm	2.70 ft-lb/in	ASTM D256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Unnotched	32.04 J/cm	60.02 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	13.0 kJ/m <sup>2</sup>	6.19 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A
	11.0 kJ/m <sup>2</sup>	5.23 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	1.50 J/cm <sup>2</sup>	7.14 ft-lb/in <sup>2</sup>	Edgew 80*10*4 sp=62mm; ISO 179/1eA
Tensile Impact Strength	577 kJ/m <sup>2</sup>	275 ft-lb/in <sup>2</sup>	Type S; ASTM D1822
Dart Drop, Total Energy	149 J	110 ft-lb	ASTM D3029
	73.0 J	53.8 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	60.0 µm/m-°C	33.3 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	

Thermal Properties	Metric	English	Comments
	@Temperature -40.0 - 95.0 °C	@Temperature -40.0 - 203 °F	ASTM E 831
CTE, linear, Transverse to Flow	60.0 µm/m-°C	33.3 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	60.0 µm/m-°C	33.3 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
Specific Heat Capacity	1.26 J/g-°C	0.301 BTU/lb-°F	ASTM C351
Thermal Conductivity	0.210 W/m-K	1.46 BTU-in/hr-ft <sup>2</sup> -°F	ASTM C177
Deflection Temperature at 1.8 MPa (264 psi)	132 °C	270 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	143 °C	289 °F	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	154 °C	309 °F	Rate B/50; ISO 306
	155 °C	311 °F	Rate B/120; ISO 306
	160 °C	320 °F	Rate B/50; ASTM D1525
UL RTI, Electrical	125 °C	257 °F	UL 746B
UL RTI, Mechanical with Impact	125 °C	257 °F	UL 746B
UL RTI, Mechanical without Impact	125 °C	257 °F	UL 746B

Optical Properties	Metric	English	Comments
Refractive Index	1.60	1.60	ASTM D542
Haze	1.0 %	1.0 %	ASTM D1003
	@Thickness 2.54 mm	@Thickness 0.100 in	
Transmission, Visible	85 %	85 %	2.54 mm; ASTM D1003

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 2.60e+17 ohm-cm	>= 2.60e+17 ohm-cm	ASTM D257
Dielectric Constant	3.0	3.0	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	

Electrical Properties	Metric	English	Comments
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	ASTM D150
Dielectric Strength	20.3 kV/mm @Thickness 3.20 mm	516 kV/in @Thickness 0.126 in	in air; ASTM D149
Dissipation Factor	0.0012 @Frequency 50.0 - 60.0 Hz	0.0012 @Frequency 50.0 - 60.0 Hz	ASTM D150
	0.024 @Frequency 100 Hz	0.024 @Frequency 100 Hz	ASTM D150
Comparative Tracking Index	175 - 250 V	175 - 250 V	UL 746A
Hot Wire Ignition, HWI	30 - 60 sec	30 - 60 sec	UL 746A
High Amp Arc Ignition, HAI	0.00 - 15 arcs	0.00 - 15 arcs	UL 746A
High Voltage Arc-Tracking Rate, HVTR	80.0 - 150 mm/min	3.15 - 5.91 in/min	UL 746A

Descriptive Properties	Value	Comments
Specific Volume	0.83cm <sup>3</sup> /g	ASTM D792

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China