

## SABIC Innovative Plastics Lexan® HPX8R PC Copolymer

Category : Polymer , Thermoplastic , Polycarbonate (PC)

### Material Notes:

Very high flow specialty polycarbonate with outstanding processability and ductility. For medical devices and pharmaceutical applications. Healthcare management of change, biocompatible (ISO10993 or USP Class VI). ETO sterilizable. Contains mold release.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-Lexan-HPX8R-PC-Copolymer.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-HPX8R-PC-Copolymer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.19 g/cc	1.19 g/cc	ASTM D792
Density	1.19 g/cc	0.0430 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption	0.0900 %	0.0900 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.12 %	0.12 %	ISO 62
Linear Mold Shrinkage, Flow	0.0040 - 0.0080 cm/cm @Thickness 3.20 mm	0.0040 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0040 - 0.0080 cm/cm @Thickness 3.20 mm	0.0040 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	35 g/10 min @Load 1.20 kg, Temperature 300 °C	35 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238
Melt Index of Compound	33 g/10 min @Load 1.20 kg, Temperature 300 °C	33 g/10 min @Load 2.65 lb, Temperature 572 °F	MVR [cm <sup>3</sup> /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell L	90	90	ASTM D785
Tensile Strength at Break	56.0 MPa	8120 psi	50 mm/min; ISO 527
	58.0 MPa	8410 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	59.0 MPa	8560 psi	Type I, 50 mm/min; ASTM D638
	59.0 MPa	8560 psi	50 mm/min; ISO 527
Elongation at Break	118.6 %	118.6 %	50 mm/min; ISO 527
	118.9 %	118.9 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	5.4 %	5.4 %	50 mm/min; ISO 527

Mechanical Properties	Metric	English	Comments
			Type I, 50 mm/min; ASTM D638
Tensile Modulus	2.36 GPa	342 ksi	50 mm/min; ASTM D638
	2.40 GPa	348 ksi	1 mm/min; ISO 527
Flexural Yield Strength	92.0 MPa	13300 psi	2 mm/min; ISO 178
	99.0 MPa	14400 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.25 GPa	326 ksi	2 mm/min; ISO 178
	2.35 GPa	341 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	7.02 J/cm	13.2 ft-lb/in	ASTM D256
	2.20 J/cm	4.12 ft-lb/in	ASTM D256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Notched (ISO)	60.0 kJ/m <sup>2</sup>	28.6 ft-lb/in <sup>2</sup>	80*10*3; ISO 180/1A
	30.0 kJ/m <sup>2</sup>	14.3 ft-lb/in <sup>2</sup>	80*10*3; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Unnotched (ISO)	NB	NB	80*10*3; ISO 180/1U
	NB	NB	80*10*3; ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact Unnotched	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	6.00 J/cm <sup>2</sup>	28.6 ft-lb/in <sup>2</sup>	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	3.00 J/cm <sup>2</sup>	14.3 ft-lb/in <sup>2</sup>	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Dart Drop, Total Energy	79.0 J	58.3 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	65.0 µm/m-°C	36.1 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 95.0 °C	@Temperature -40.0 - 203 °F	

Thermal Properties	Metric $m/m-^{\circ}C$	English $in-^{\circ}F$	Comments
	@Temperature 23.0 - 80.0 $^{\circ}C$	@Temperature 73.4 - 176 $^{\circ}F$	ISO 11359-2
CTE, linear, Transverse to Flow	74.0 $\mu m/m-^{\circ}C$	41.1 $\mu in/in-^{\circ}F$	ASTM E 831
	@Temperature -40.0 - 95.0 $^{\circ}C$	@Temperature -40.0 - 203 $^{\circ}F$	
	74.0 $\mu m/m-^{\circ}C$	41.1 $\mu in/in-^{\circ}F$	ISO 11359-2
Deflection Temperature at 1.8 MPa (264 psi)	@Temperature 23.0 - 80.0 $^{\circ}C$	@Temperature 73.4 - 176 $^{\circ}F$	ISO 11359-2
	117 $^{\circ}C$	243 $^{\circ}F$	Flatw 80*10*4 sp=64mm; ISO 75/Af
	120 $^{\circ}C$	248 $^{\circ}F$	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Vicat Softening Point	137 $^{\circ}C$	279 $^{\circ}F$	Rate B/50; ISO 306
	138 $^{\circ}C$	280 $^{\circ}F$	Rate A/50; ASTM D1525
	140 $^{\circ}C$	284 $^{\circ}F$	Rate B/120; ISO 306
UL RTI, Electrical	130 $^{\circ}C$	266 $^{\circ}F$	UL 746B
UL RTI, Mechanical without Impact	130 $^{\circ}C$	266 $^{\circ}F$	UL 746B
Flammability, UL94	HB	HB	UL 94
	@Thickness 1.50 mm	@Thickness 0.0591 in	
Glow Wire Test	825 $^{\circ}C$	1520 $^{\circ}F$	IEC 60695-2-13
	850 $^{\circ}C$	1560 $^{\circ}F$	IEC 60695-2-13
	960 $^{\circ}C$	1760 $^{\circ}F$	IEC 60695-2-12
@Thickness 3.00 mm	@Thickness 0.118 in		

Optical Properties	Metric	English	Comments
Haze	3.0 %	3.0 %	ASTM D1003
	@Thickness 2.54 mm	@Thickness 0.100 in	
Transmission, Visible	82 %	82 %	2.54 mm; ASTM D1003

Electrical Properties	Metric	English	Comments
Volume Resistivity	$\geq 1.00e+15$ ohm-cm	$\geq 1.00e+15$ ohm-cm	ASTM D257
Surface Resistance	$\geq 1.00e+15$ ohm	$\geq 1.00e+15$ ohm	ASTM D257

Descriptive Properties	Value	Comments
Ball Pressure Test, 125°C +/- 2°C	PASS	IEC 60695-10-2

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China