

SABIC Innovative Plastics Lexan® LGK4030 PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-LGK4030-PC-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.54 g/cc	1.54 g/cc	ASTM D792
Water Absorption	0.14 % @Time 86400 sec	0.14 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0015 - 0.0020 cm/cm @Thickness 3.20 mm	0.0015 - 0.0020 in/in @Thickness 0.126 in	SABIC Method

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	91	91	ASTM D785
Tensile Strength, Yield	129 MPa	18700 psi	SABIC - Japan Method
Elongation at Break	3.0 - 5.0 %	3.0 - 5.0 %	SABIC - Japan Method
Flexural Strength	180 MPa	26100 psi	ASTM D790
Flexural Modulus	8.82 GPa	1280 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm	2.00 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	22.0 - 43.0 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$ @Temperature -30.0 - 30.0 $^\circ\text{C}$	12.2 - 23.9 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$ @Temperature -22.0 - 86.0 $^\circ\text{F}$	TMA
Deflection Temperature at 0.46 MPa (66 psi)	145 $^\circ\text{C}$ @Thickness 3.20 mm	293 $^\circ\text{F}$ @Thickness 0.126 in	unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Surface Resistance	1.00e+16 ohm	1.00e+16 ohm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China