

SABIC Innovative Plastics Lexan® LR180 PC (Europe-Africa-Middle East)

Category : Polymer , Renewable/Recycled Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

LR180 is a medium viscosity, non UV, non release containing multipurpose polycarbonate recycle grade This data was supplied by SABIC-IP for the Europe-Africa-Middle East region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-LR180-PC-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.15 %	0.15 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.35 % @Temperature 23.0 °C	0.35 % @Temperature 73.4 °F	ISO 62
Melt Flow	12 g/10 min @Load 1.20 kg, Temperature 300 °C	12 g/10 min @Load 2.65 lb, Temperature 572 °F	[cm ³ /10 min] Melt Volume Rate; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	65.0 MPa	9430 psi	50 mm/min; ISO 527
Tensile Strength, Yield	60.0 MPa	8700 psi	50 mm/min; ISO 527
Elongation at Break	100 %	100 %	50 mm/min; ISO 527
Elongation at Yield	6.0 %	6.0 %	50 mm/min; ISO 527
Tensile Modulus	2.30 GPa	334 ksi	1 mm/min; ISO 527
Flexural Yield Strength	90.0 MPa	13100 psi	2 mm/min; ISO 178
Flexural Modulus	2.25 GPa	326 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	11.0 kJ/m ² @Temperature -30.0 °C	5.23 ft-lb/in ² @Temperature -22.0 °F	80*10*3; ISO 180/1A
	65.0 kJ/m ² @Temperature 23.0 °C	30.9 ft-lb/in ² @Temperature 73.4 °F	80*10*3; ISO 180/1A
Izod Impact, Unnotched (ISO)	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	80*10*3; ISO 180/1U
	NB	NB	80*10*3; ISO 180/1U

Mechanical Properties	@Temperature -30.0 °C Metric	@Temperature -22.0 °F English	Comments
Charpy Impact Unnotched	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	NB @Temperature -30.0 °C	NB @Temperature -22.0 °F	Edgew 80*10*3 sp=62mm; ISO 179/1eU
Charpy Impact, Notched	1.20 J/cm² @Temperature -30.0 °C	5.71 ft-lb/in² @Temperature -22.0 °F	V-notch Edgew 80*10*3 sp=62mm; ISO 179/1eA
	6.50 J/cm² @Temperature 23.0 °C	30.9 ft-lb/in² @Temperature 73.4 °F	V-notch Edgew 80*10*3 sp=62mm; ISO 179/1eA

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 µm/m-°C @Temperature -40.0 - 40.0 °C	38.9 µin/in-°F @Temperature -40.0 - 104 °F	ISO 11359-2
CTE, linear, Transverse to Flow	70.0 µm/m-°C @Temperature -40.0 - 40.0 °C	38.9 µin/in-°F @Temperature -40.0 - 104 °F	ISO 11359-2
Deflection Temperature at 1.8 MPa (264 psi)	124 °C	255 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
Vicat Softening Point	141 °C	286 °F	Rate B/50; ISO 306
	143 °C	289 °F	Rate B/120; ISO 306

Optical Properties	Metric	English	Comments
Refractive Index	1.586	1.586	ASTM D 542
Haze	<= 1.0 % @Thickness 2.54 mm	<= 1.0 % @Thickness 0.100 in	ASTM D 1003
Transmission, Visible	87 % @Thickness 2.54 mm	87 % @Thickness 0.100 in	ASTM D 1003

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China