

SABIC Innovative Plastics Lexan® LUX9616G PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Lexan LUX9616G is a flame retardant polycarbonate featuring non brominated and non chlorinated FR system with diffusion effective and thin wall FR performance. It intended to meet WEEE/RoHS requirements for various applications.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-LUX9616G-PC-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183
Moisture Absorption	0.150 %	0.150 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.35 %	0.35 %	ISO 62
Linear Mold Shrinkage, Flow	0.0060 - 0.0080 cm/cm @Thickness 3.20 mm	0.0060 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	7.0 g/10 min @Load 1.20 kg, Temperature 300 °C	7.0 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	58.0 MPa	8410 psi	50 mm/min; ISO 527
	65.0 MPa	9430 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	62.0 MPa	8990 psi	Type I, 50 mm/min; ASTM D638
	62.0 MPa	8990 psi	50 mm/min; ISO 527
Elongation at Break	75 %	75 %	50 mm/min; ISO 527
	80 %	80 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	6.0 %	6.0 %	Type I, 50 mm/min; ASTM D638
	6.0 %	6.0 %	50 mm/min; ISO 527
Tensile Modulus	2.23 GPa	323 ksi	1 mm/min; ISO 527
	2.30 GPa	334 ksi	5 mm/min; ASTM D638
Flexural Strength	95.0 MPa	13800 psi	12.5 mm/min; ISO 178
	95.0 MPa	13800 psi	1.3 mm/min, 50 mm span; ASTM

Flexural Yield Strength Mechanical Properties	Metric	English	D790 Comments
Flexural Modulus	2.16 GPa	313 ksi	1.3 mm/min, 50 mm span; ASTM D790
	2.25 GPa	326 ksi	2 mm/min; ISO 178
Izod Impact, Notched	1.50 J/cm	2.81 ft-lb/in	ASTM D256
Izod Impact, Notched (ISO)	15.0 kJ/m ²	7.14 ft-lb/in ²	80*10*3; ISO 180/1A
Dart Drop, Total Energy	70.0 J	51.6 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	68.0 µm/m-°C	37.8 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
CTE, linear, Transverse to Flow	67.0 µm/m-°C	37.2 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
Deflection Temperature at 1.8 MPa (264 psi)	125 °C	257 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	125 °C	257 °F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Vicat Softening Point	141 °C	286 °F	Rate B/50; ASTM D1525
Flammability, UL94	V-0	V-0	UL 94
	@Thickness 1.50 mm	@Thickness 0.0591 in	
Glow Wire Test	850 °C	1560 °F	IEC 60695-2-13
	850 °C	1560 °F	IEC 60695-2-13
	960 °C	1760 °F	IEC 60695-2-12
	@Thickness 1.00 mm	@Thickness 0.0394 in	

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	175 - 250 V	175 - 250 V	UL 746A
Hot Wire Ignition, HWI	15 - 30 sec	15 - 30 sec	UL 746A
High Amp Arc Ignition, HAI	60 - 120 arcs	60 - 120 arcs	UL 746A

Descriptive Properties	Value	Comments
Ball Pressure Test, 125°C +/- 2°C	PASSES	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China