

SABIC Innovative Plastics Lexan® ML4351 PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-ML4351-PC-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.28 g/cc	1.28 g/cc	ASTM D792
Water Absorption	0.15 % @Time 86400 sec	0.15 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	61.0 MPa	8850 psi	SABIC - Japan Method
Elongation at Break	190 %	190 %	SABIC - Japan Method
Flexural Strength	93.0 MPa	13500 psi	ASTM D790
Flexural Modulus	2.35 GPa	341 ksi	ASTM D790
Izod Impact, Notched	4.90 J/cm	9.18 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	70.0 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$ @Temperature -30.0 - 30.0 $^\circ\text{C}$	38.9 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$ @Temperature -22.0 - 86.0 $^\circ\text{F}$	TMA
Deflection Temperature at 0.46 MPa (66 psi)	132 $^\circ\text{C}$ @Thickness 3.20 mm	270 $^\circ\text{F}$ @Thickness 0.126 in	unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Surface Resistance	1.00e+16 ohm	1.00e+16 ohm	ASTM D257
Dielectric Constant	3.2 @Frequency 50.0 - 60.0 Hz	3.2 @Frequency 50.0 - 60.0 Hz	ASTM D150

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China