

SABIC Innovative Plastics NORYL EXT130 PPE+HIPS (Asia Pacific)

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polystyrene (PS)

Material Notes:

PPE+PS for auto exterior, High heat

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-NORYL-EXT130-PPEHIPS-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.06 g/cc	1.06 g/cc	ASTM D792
Water Absorption	0.060 %	0.060 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	
Melt Flow	3.8 g/10 min	3.8 g/10 min	ASTM D1238
	@Load 10.0 kg, Temperature 250 Â°C	@Load 22.0 lb, Temperature 482 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	54.0 MPa	7830 psi	SABIC - Japan Method
Elongation at Break	100 %	100 %	SABIC - Japan Method
Flexural Strength	76.0 MPa	11000 psi	ASTM D790
Flexural Modulus	2.25 GPa	326 ksi	ASTM D790
Izod Impact, Notched	1.47 J/cm	2.75 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	65.0 Âµm/m-Â°C	36.1 Âµin/in-Â°F	TMA
	@Temperature -30.0 - 30.0 Â°C	@Temperature -22.0 - 86.0 Â°F	
Deflection Temperature at 1.8 MPa (264 psi)	130 Â°C	266 Â°F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China