

SABIC Innovative Plastics NORYL GTX GTX910 PPE+PS+PA (Asia Pacific)

Category : Polymer , Thermoplastic , Nylon , Polyphenylene Ether/PPO , Polystyrene (PS)

Material Notes:

Unfilled grade for automotive on-line painted components. Dimensional stability. Excellent chemical resistance. Class A surface appearance.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-NORYL-GTX-GTX910-PPEPSA-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.10 g/cc	1.10 g/cc	ASTM D792
Density	1.107 g/cc	0.03999 lb/in ³	ASTM D792
Moisture Absorption	0.500 %	0.500 %	50% RH, 24 hrs; ASTM D570
Moisture Absorption at Equilibrium	1.0 %	1.0 %	50% RH; ASTM D570
Linear Mold Shrinkage, Flow	0.016 - 0.018 cm/cm	0.016 - 0.018 in/in	annealed 130C 1hr; ASTM D955
	0.011 - 0.013 cm/cm	0.011 - 0.013 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	
Linear Mold Shrinkage, Transverse	0.010 - 0.012 cm/cm	0.010 - 0.012 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	116	116	ASTM D785
Tensile Strength at Break	55.0 MPa	7980 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	59.0 MPa	8560 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	60 %	60 %	Type I, 50 mm/min; ASTM D638
Flexural Yield Strength	95.0 MPa	13800 psi	2.6 mm/min, 100 mm span; ASTM D790
Flexural Modulus	2.24 GPa	325 ksi	2.6 mm/min, 100 mm span; ASTM D790
Izod Impact, Notched	2.40 J/cm	4.50 ft-lb/in	ASTM D256
	1.33 J/cm	2.49 ft-lb/in	ASTM D256
	@Temperature -30.0 Å°C	@Temperature -22.0 Å°F	
Dart Drop, Total Energy	50.0 J	36.9 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763

Mechanical Properties	Metric	English ^{lb}	Comments
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	Instrumented Impact Energy @ peak, ASTM D3763

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	90.0 Âµm/m-Â°C	50.0 Âµin/in-Â°F	ASTM E 831
	@Temperature -40.0 - 95.0 Â°C	@Temperature -40.0 - 203 Â°F	
	126 Âµm/m-Â°C	70.0 Âµin/in-Â°F	ASTM E 831
	@Temperature 60.0 - 138 Â°C	@Temperature 140 - 280 Â°F	
CTE, linear, Transverse to Flow	90.0 Âµm/m-Â°C	50.0 Âµin/in-Â°F	ASTM E 831
	@Temperature -40.0 - 95.0 Â°C	@Temperature -40.0 - 203 Â°F	
	126 Âµm/m-Â°C	70.0 Âµin/in-Â°F	ASTM E 831
	@Temperature 60.0 - 138 Â°C	@Temperature 140 - 280 Â°F	
Deflection Temperature at 0.46 MPa (66 psi)	193 Â°C	379 Â°F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Deflection Temperature at 1.8 MPa (264 psi)	143 Â°C	289 Â°F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Vicat Softening Point	232 Â°C	450 Â°F	Rate B/50; ASTM D1525
UL RTI, Electrical	50.0 Â°C	122 Â°F	UL 746B
UL RTI, Mechanical with Impact	50.0 Â°C	122 Â°F	UL 746B
UL RTI, Mechanical without Impact	50.0 Â°C	122 Â°F	UL 746B
Flammability, UL94	HB	HB	UL 94
	@Thickness 1.49 mm	@Thickness 0.0587 in	

Electrical Properties	Metric	English	Comments
Arc Resistance	0.00 - 60 sec	0.00 - 60 sec	Tungsten; ASTM D495
Comparative Tracking Index	400 - 600 V	400 - 600 V	UL 746A
Hot Wire Ignition, HWI	15 - 30 sec	15 - 30 sec	UL 746A
High Amp Arc Ignition, HAI	>= 120 arcs	>= 120 arcs	UL 746A
High Voltage Arc-Tracking Rate,	>= 150 mm/min	>= 5.91 in/min	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China