

## SABIC Innovative Plastics NORYL GTX GTX974 PPE+PA (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Nylon , Polyphenylene Ether/PPO

### Material Notes:

NORYL GTX974 is a material especially designed for in- or on-line painted bodypanels and fenders in particular. This material combines impact performance with conductivity for electro-static painting in an unique way.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-NORYL-GTX-GTX974-PPEPA-Europe-Africa-Middle-East.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-NORYL-GTX-GTX974-PPEPA-Europe-Africa-Middle-East.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.08 g/cc	1.08 g/cc	ASTM D792
Density	1.08 g/cc	0.0390 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption	1.20 %	1.20 %	23 <sup>o</sup> C / 50% RH; ISO 62
Water Absorption at Saturation	4.2 %	4.2 %	ISO 62
Linear Mold Shrinkage, Flow	0.013 - 0.016 cm/cm @Thickness 3.20 mm	0.013 - 0.016 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.011 - 0.014 cm/cm @Thickness 3.20 mm	0.011 - 0.014 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	10 g/10 min @Load 5.00 kg, Temperature 280 <sup>o</sup> C	10 g/10 min @Load 11.0 lb, Temperature 536 <sup>o</sup> F	ASTM D1238
Melt Index of Compound	12 g/10 min @Load 5.00 kg, Temperature 280 <sup>o</sup> C	12 g/10 min @Load 11.0 lb, Temperature 536 <sup>o</sup> F	MVR [cm <sup>3</sup> /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	45.0 MPa	6530 psi	50 mm/min; ISO 527
	50.0 MPa	7250 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	50.0 MPa	7250 psi	50 mm/min; ISO 527
	55.0 MPa	7980 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	30 %	30 %	50 mm/min; ISO 527
	50 %	50 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	4.0 %	4.0 %	50 mm/min; ISO 527

Mechanical Properties	Metric	English	Comments
Tensile Modulus	2.00 GPa	290 ksi	1 mm/min; ISO 527
	2.05 GPa	297 ksi	50 mm/min; ASTM D638
Flexural Yield Strength	75.0 MPa	10900 psi	2 mm/min; ISO 178
	80.0 MPa	11600 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	1.90 GPa	276 ksi	2 mm/min; ISO 178
	2.05 GPa	297 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	1.80 J/cm	3.37 ft-lb/in	ASTM D256
	1.20 J/cm @Temperature -30.0 °C	2.25 ft-lb/in @Temperature -22.0 °F	ASTM D256
Izod Impact, Notched (ISO)	17.0 kJ/m <sup>2</sup>	8.09 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A
	10.0 kJ/m <sup>2</sup> @Temperature -30.0 °C	4.76 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	80*10*4; ISO 180/1A
Charpy Impact, Notched	1.80 J/cm <sup>2</sup>	8.57 ft-lb/in <sup>2</sup>	Edgew 80*10*4 sp=62mm; ISO 179/1eA
	1.00 J/cm <sup>2</sup> @Temperature -30.0 °C	4.76 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	Edgew 80*10*4 sp=62mm; ISO 179/1eA
Dart Drop, Total Energy	50.0 J @Temperature 23.0 °C	36.9 ft-lb @Temperature 73.4 °F	ASTM D3763

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	90.0 μm/m-°C	50.0 μin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
CTE, linear, Transverse to Flow	100 μm/m-°C	55.6 μin/in-°F	ISO 11359-2
	@Temperature 23.0 - 60.0 °C	@Temperature 73.4 - 140 °F	
CTE, linear, Transverse to Flow	90.0 μm/m-°C	50.0 μin/in-°F	ISO 11359-2
	@Temperature 23.0 - 60.0 °C	@Temperature 73.4 - 140 °F	

Thermal Properties	Metric	English	Comments
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	ASTM E 631
Deflection Temperature at 0.46 MPa (66 psi)	175 Å°C	347 Å°F	Edgew 120*10*4 sp=100mm; ISO 75/Be
	180 Å°C	356 Å°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Vicat Softening Point	175 Å°C	347 Å°F	Rate B/50; ISO 306
	180 Å°C	356 Å°F	Rate B/120; ISO 306
	180 Å°C	356 Å°F	Rate B/50; ASTM D1525
	230 Å°C	446 Å°F	Rate A/50; ISO 306
Flammability, UL94	HB	HB	UL 94
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	HB	HB	UL 94
	@Thickness 3.00 mm	@Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1000 - 10000 ohm-cm	1000 - 10000 ohm-cm	SABIC Method

Descriptive Properties	Value	Comments
Ball Pressure Test, 125Å°C +/- 2Å°C	PASSES	IEC 60695-10-2

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China