

SABIC Innovative Plastics NORYL GTX GTX985 PPE+PA66 (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Polyphenylene Ether/PPO

Material Notes:

NORYL GTX985 is a 18% mineral filled material. This material combines high stiffness and excellent temperature resistance with conductivity for electrostatic painting.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-NORYL-GTX-GTX985-PPEPA66-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.25 g/cc	1.25 g/cc	ASTM D792
Density	1.25 g/cc	0.0452 lb/in ³	ISO 1183
Moisture Absorption	1.10 %	1.10 %	23 ^o C / 50% RH; ISO 62
Linear Mold Shrinkage, Flow	0.011 cm/cm @Thickness 3.20 mm	0.011 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	16 g/10 min @Load 5.00 kg, Temperature 280 ^o C	16 g/10 min @Load 11.0 lb, Temperature 536 ^o F	ASTM D1238
Melt Index of Compound	15 g/10 min @Load 5.00 kg, Temperature 280 ^o C	15 g/10 min @Load 11.0 lb, Temperature 536 ^o F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	60.0 MPa	8700 psi	Type I, 5 mm/min; ASTM D638
	60.0 MPa	8700 psi	5 mm/min; ISO 527
Tensile Strength, Yield	65.0 MPa	9430 psi	Type I, 5 mm/min; ASTM D638
	65.0 MPa	9430 psi	5 mm/min; ISO 527
Elongation at Break	7.0 %	7.0 %	Type I, 5 mm/min; ASTM D638
	7.0 %	7.0 %	5 mm/min; ISO 527
Elongation at Yield	4.0 %	4.0 %	Type I, 5 mm/min; ASTM D638
	4.0 %	4.0 %	5 mm/min; ISO 527
Tensile Modulus	4.40 GPa	638 ksi	1 mm/min; ISO 527
Flexural Yield Strength	105 MPa	15200 psi	2 mm/min; ISO 178

Mechanical Properties	Metric 110 MPa	English 16000 psi	Comments 1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	4.20 GPa	609 ksi	1.3 mm/min, 50 mm span; ASTM D790
	4.35 GPa	631 ksi	2 mm/min; ISO 178
Izod Impact, Notched	0.450 J/cm	0.843 ft-lb/in	ASTM D256
	0.400 J/cm	0.749 ft-lb/in	ASTM D256
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
Izod Impact, Notched (ISO)	4.00 kJ/mÂ²	1.90 ft-lb/inÂ²	80*10*4; ISO 180/1A
	4.00 kJ/mÂ²	1.90 ft-lb/inÂ²	80*10*4; ISO 180/1A
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
Izod Impact, Unnotched (ISO)	60.0 kJ/mÂ²	28.6 ft-lb/inÂ²	80*10*3; ISO 180/1U
	55.0 kJ/mÂ²	26.2 ft-lb/inÂ²	80*10*3; ISO 180/1U
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
Charpy Impact, Notched	0.400 J/cmÂ²	1.90 ft-lb/inÂ²	Edgew 80*10*4 sp=62mm; ISO 179/1eA
Dart Drop, Total Energy	10.0 J	7.38 ft-lb	ASTM D3763
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	60.0 Âµm/m-Â°C	33.3 Âµin/in-Â°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Â°C	@Temperature 73.4 - 140 Â°F	
CTE, linear, Transverse to Flow	65.0 Âµm/m-Â°C	36.1 Âµin/in-Â°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Â°C	@Temperature 73.4 - 140 Â°F	
Deflection Temperature at 0.46 MPa (66 psi)	205 Â°C	401 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
	200 Â°C	392 Â°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Vicat Softening Point	195 Â°C	383 Â°F	Rate B/50; ASTM D1525
	195 Â°C	383 Â°F	Rate B/50; ISO 306

Thermal Properties

Metric

English

Comments ISO 306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China