

## SABIC Innovative Plastics NORYL GTX870 PPE+PA6 (Asia Pacific)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Polyphenylene Ether/PPO

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-NORYL-GTX870-PPEPA6-Asia-Pacific.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-NORYL-GTX870-PPEPA6-Asia-Pacific.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	ASTM D792
Water Absorption	0.50 %	0.50 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0040 - 0.0080 cm/cm	0.0040 - 0.0080 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	117 MPa	17000 psi	SABIC - Japan Method
	122 MPa	17700 psi	
Elongation at Break	5.0 %	5.0 %	Type I, 5 mm/min; ASTM D638
	12 %	12 %	
Flexural Strength	166 MPa	24100 psi	ASTM D790
Flexural Modulus	5.68 GPa	824 ksi	ASTM D790
Izod Impact, Notched	1.17 J/cm	2.19 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	40.0 - 60.0 $\mu\text{m/m}\cdot\text{Å}^\circ\text{C}$	22.2 - 33.3 $\mu\text{in/in}\cdot\text{Å}^\circ\text{F}$	TMA
	@Temperature -30.0 - 30.0 $\text{Å}^\circ\text{C}$	@Temperature -22.0 - 86.0 $\text{Å}^\circ\text{F}$	
Deflection Temperature at 1.8 MPa (264 psi)	200 $\text{Å}^\circ\text{C}$	392 $\text{Å}^\circ\text{F}$	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China