

SABIC Innovative Plastics NORYL PX0888 PPE+PS (Asia Pacific)

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polystyrene (PS)

Material Notes:

Unfilled, non-FR. Higher heat resistance than N110 (BOZ) and px0844 (USA). For automotive interiors. 250F (121C) DTUL.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-NORYL-PX0888-PPEPS-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Water Absorption	0.10 %	0.10 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	
Melt Index of Compound	6.0 g/10 min	6.0 g/10 min	MVR [cm ³ /10 min]; ISO 1133
	@Load 2.16 kg, Temperature 300 Â°C	@Load 4.76 lb, Temperature 572 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength, Yield	58.0 MPa	8410 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	30 %	30 %	Type I, 50 mm/min; ASTM D638
Flexural Yield Strength	93.0 MPa	13500 psi	2.6 mm/min, 100 mm span; ASTM D790
Flexural Modulus	2.35 GPa	341 ksi	2.6 mm/min, 100 mm span; ASTM D790
Izod Impact, Notched	1.97 J/cm	3.69 ft-lb/in	ASTM D256
	1.33 J/cm	2.49 ft-lb/in	
	@Temperature -40.0 Â°C	@Temperature -40.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	73.8 Âµm/m-Â°C	41.0 Âµin/in-Â°F	ASTM E 831
	@Temperature 0.000 - 100 Â°C	@Temperature 32.0 - 212 Â°F	
Deflection Temperature at 0.46 MPa	129 Â°C	264 Â°F	unannealed; ASTM D648

<small>(56 psi)</small> Thermal Properties	@Thickness 6.40 mm Metric	@Thickness 0.252 in English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	127 Å°C @Thickness 6.40 mm	261 Å°F @Thickness 0.252 in	unannealed; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China