

SABIC Innovative Plastics NORYL PX2630 PPE+HIPS (Asia Pacific)

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polystyrene (PS)

Material Notes:

PPE+HIPS Unfilled high Impact

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-NORYL-PX2630-PPEHIPS-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.06 g/cc	1.06 g/cc	ASTM D792
Melt Flow	3.8 g/10 min	3.8 g/10 min	ASTM D1238
	@Load 10.0 kg, Temperature 250 °C	@Load 22.0 lb, Temperature 482 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	48.0 MPa	6960 psi	SABIC - Japan Method
Elongation at Break	42 %	42 %	SABIC - Japan Method
Flexural Strength	76.0 MPa	11000 psi	ASTM D790
Flexural Modulus	2.09 GPa	303 ksi	ASTM D790
Izod Impact, Notched	3.30 J/cm	6.18 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	126 °C	259 °F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China