

SABIC Innovative Plastics Noryl EN130P PPE+PS (Asia Pacific)

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polystyrene (PS)

Material Notes:

High heat, extrusion grade PPO/HIPS alloy. This data was supplied by SABIC-IP for the Asia Pacific region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Noryl-EN130P-PPEPS-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.06 g/cc	1.06 g/cc	ASTM D 792
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	50.0 MPa	7250 psi	Type I, 50 mm/min; ASTM D 638
Elongation at Break	30 %	30 %	Type I, 50 mm/min; ASTM D 638
Flexural Yield Strength	93.0 MPa	13500 psi	1.3 mm/min, 50 mm span; ASTM D 790
Flexural Modulus	2.00 GPa	290 ksi	1.3 mm/min, 50 mm span; ASTM D 790
Izod Impact, Notched	2.40 J/cm @Temperature 23.0 Â°C	4.50 ft-lb/in @Temperature 73.4 Â°F	ASTM D 256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	121 Â°C @Thickness 3.20 mm	250 Â°F @Thickness 0.126 in	unannealed; ASTM D 648
	125 Â°C @Thickness 6.40 mm	257 Â°F @Thickness 0.252 in	unannealed; ASTM D 648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China