

SABIC Innovative Plastics Noryl GTX GTX8110P PPE+PA (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Nylon , Polyphenylene Ether/PPO

Material Notes:

GTX8110P is a glass filled extrudable Noryl GTX with low thermal conductivity, suitable for thermal breaks. This data was supplied by SABIC-IP for the Europe-Africa-Middle East region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Noryl-GTX-GTX8110P-PPEPA-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.17 g/cc	0.0423 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	1.1 %	1.1 %	23 ^o C / 50% RH; ISO 62
Water Absorption at Saturation	3.0 % @Temperature 23.0 ^o C	3.0 % @Temperature 73.4 ^o F	ISO 62
Melt Flow	5.0 g/10 min @Load 10.0 kg, Temperature 280 ^o C	5.0 g/10 min @Load 22.0 lb, Temperature 536 ^o F	[cm ³ /10 min] Melt Volume Rate; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	95.0 MPa	13800 psi	5 mm/min; ISO 527
Tensile Strength, Yield	100 MPa	14500 psi	5 mm/min; ISO 527
Elongation at Break	5.0 %	5.0 %	5 mm/min; ISO 527
Elongation at Yield	4.0 %	4.0 %	5 mm/min; ISO 527
Tensile Modulus	4.50 GPa	653 ksi	1 mm/min; ISO 527
Flexural Yield Strength	135 MPa	19600 psi	2 mm/min; ISO 178
Flexural Modulus	3.40 GPa	493 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	6.00 kJ/m ² @Temperature -30.0 ^o C	2.86 ft-lb/in ² @Temperature -22.0 ^o F	80*10*4; ISO 180/1A
	7.00 kJ/m ² @Temperature 23.0 ^o C	3.33 ft-lb/in ² @Temperature 73.4 ^o F	80*10*4; ISO 180/1A
Charpy Impact, Notched	0.800 J/cm ²	3.81 ft-lb/in ²	V-notch Edgew 80*10*4 sp=62mm;

Mechanical Properties	Metric @Temperature 23.0 Â°C	English @Temperature 73.4 Â°F	ISO 179/1eA Comments
Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	53.0 Âµm/m-Â°C @Temperature 23.0 - 60.0 Â°C	29.4 Âµin/in-Â°F @Temperature 73.4 - 140 Â°F	ISO 11359-2
CTE, linear, Transverse to Flow	72.0 Âµm/m-Â°C @Temperature 23.0 - 60.0 Â°C	40.0 Âµin/in-Â°F @Temperature 73.4 - 140 Â°F	ISO 11359-2
Deflection Temperature at 0.46 MPa (66 psi)	205 Â°C	401 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
Vicat Softening Point	225 Â°C	437 Â°F	Rate B/50; ISO 306
	225 Â°C	437 Â°F	Rate B/120; ISO 306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China