

SABIC Innovative Plastics Noryl GTX GTX977 PPE+PA66 (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polyester, TP , Polyphenylene Ether/PPO

Material Notes:

Noryl GTX GTX977 resin is a mineral reinforced conductive Noryl GTX with a improved CTE (7) with a balanced performance of Impact and stiffness. (developmental grade : EXNX0074)This data was supplied by SABIC-IP for the Europe-Africa-Middle East region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Noryl-GTX-GTX977-PPEPA66-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.30 g/cc	1.30 g/cc	ASTM D 792
Density	1.30 g/cc	0.0470 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.80 %	0.80 %	23 ^o C / 50% RH; ISO 62
Water Absorption at Saturation	3.5 % @Temperature 23.0 ^o C	3.5 % @Temperature 73.4 ^o F	ISO 62
Linear Mold Shrinkage, Flow	0.010 - 0.013 cm/cm @Thickness 3.20 mm	0.010 - 0.013 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.010 - 0.013 cm/cm @Thickness 3.20 mm	0.010 - 0.013 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	9.0 g/10 min @Load 5.00 kg, Temperature 280 ^o C	9.0 g/10 min @Load 11.0 lb, Temperature 536 ^o F	ASTM D 1238
	11 g/10 min @Load 5.00 kg, Temperature 280 ^o C	11 g/10 min @Load 11.0 lb, Temperature 536 ^o F	[cm ³ /10 min] Melt Volume Rate; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	62.0 MPa	8990 psi	Type I, 5 mm/min; ASTM D 638
	65.0 MPa	9430 psi	50 mm/min; ISO 527
Tensile Strength, Yield	65.0 MPa	9430 psi	Type I, 5 mm/min; ASTM D 638
	65.0 MPa	9430 psi	50 mm/min; ISO 527
Elongation at Break	12 %	12 %	50 mm/min; ISO 527
	18 %	18 %	Type I, 5 mm/min; ASTM D 638

Mechanical Properties	Metric	English	Comments
Elongation at Yield	9.0 %	9.0 %	Type I, 5 mm/min; ASTM D 638
	9.0 %	9.0 %	50 mm/min; ISO 527
Tensile Modulus	3.40 GPa	493 ksi	1 mm/min; ISO 527
	3.90 GPa	566 ksi	5 mm/min; ASTM D 638
Flexural Yield Strength	100 MPa	14500 psi	2 mm/min; ISO 178
	110 MPa	16000 psi	1.3 mm/min, 50 mm span; ASTM D 790
Flexural Modulus	3.30 GPa	479 ksi	2 mm/min; ISO 178
	3.70 GPa	537 ksi	1.3 mm/min, 50 mm span; ASTM D 790
Izod Impact, Notched	0.650 J/cm	1.22 ft-lb/in	ASTM D 256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	0.900 J/cm	1.69 ft-lb/in	ASTM D 256
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Izod Impact, Notched (ISO)	6.00 kJ/m ²	2.86 ft-lb/in ²	80*10*4; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	11.0 kJ/m ²	5.23 ft-lb/in ²	80*10*4; ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Izod Impact, Unnotched (ISO)	120 kJ/m ²	57.1 ft-lb/in ²	80*10*4; ISO 180/1U
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	NB	NB	80*10*4; ISO 180/1U
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.600 J/cm ²	2.86 ft-lb/in ²	V-notch Edgew 80*10*4 sp=62mm; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	1.00 J/cm ²	4.76 ft-lb/in ²	V-notch Edgew 80*10*4 sp=62mm; ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Impact Test	5.00 J	3.69 ft-lb	Instrumented Impact Total Energy;

Mechanical Properties	@Temperature 23.0 Metric °C	@Temperature 73.4 °F English	ASTM D 3763 Comments
Thermal Properties			
CTE, linear, Parallel to Flow	70.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature 23.0 - 60.0 $\text{Å}^\circ\text{C}$	38.9 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature 73.4 - 140 $\text{Å}^\circ\text{F}$	ISO 11359-2
CTE, linear, Transverse to Flow	80.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature 23.0 - 60.0 $\text{Å}^\circ\text{C}$	44.4 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature 73.4 - 140 $\text{Å}^\circ\text{F}$	ISO 11359-2
Deflection Temperature at 0.46 MPa (66 psi)	195 $\text{Å}^\circ\text{C}$	383 $\text{Å}^\circ\text{F}$	Flatw 80*10*4 sp=64mm; ISO 75/Bf
	199 $\text{Å}^\circ\text{C}$	390 $\text{Å}^\circ\text{F}$	Edgew 120*10*4 sp=100mm; ISO 75/Be
	212 $\text{Å}^\circ\text{C}$ @Thickness 3.20 mm	414 $\text{Å}^\circ\text{F}$ @Thickness 0.126 in	unannealed; ASTM D 648
Vicat Softening Point	200 $\text{Å}^\circ\text{C}$	392 $\text{Å}^\circ\text{F}$	Rate B/120; ISO 306
	202 $\text{Å}^\circ\text{C}$	396 $\text{Å}^\circ\text{F}$	Rate B/50; ISO 306
	205 $\text{Å}^\circ\text{C}$	401 $\text{Å}^\circ\text{F}$	Rate B/50; ASTM D 1525
Electrical Properties			
Volume Resistivity	1000 - 10000 ohm-cm	1000 - 10000 ohm-cm	SABIC Method

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China