

SABIC Innovative Plastics ULTEM 1000R PEI (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polyetherimide (PEI)

Material Notes:

Standard flow Polyetherimide (Tg 217C) with internal mold release. Resin is RoHS compliant. UL94 V0, V2 and 5VA listing.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-ULTEM-1000R-PEI-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.27 g/cc	0.0459 lb/in ³	ISO 1183
Moisture Absorption	0.700 %	0.700 %	23 ^o C / 50% RH; ISO 62
Water Absorption at Saturation	1.25 %	1.25 %	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	on Tensile Bar; SABIC Method
Melt Index of Compound	13 g/10 min @Load 5.00 kg, Temperature 360 ^o C	13 g/10 min @Load 11.0 lb, Temperature 680 ^o F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, H358/30	140 MPa	20300 psi	ISO 2039-1
Tensile Strength at Break	85.0 MPa	12300 psi	50 mm/min; ISO 527
Tensile Strength, Yield	105 MPa	15200 psi	50 mm/min; ISO 527
Elongation at Break	60 %	60 %	50 mm/min; ISO 527
Elongation at Yield	6.0 %	6.0 %	50 mm/min; ISO 527
Tensile Modulus	3.20 GPa	464 ksi	1 mm/min; ISO 527
Flexural Yield Strength	160 MPa	23200 psi	2 mm/min; ISO 178
Flexural Modulus	3.30 GPa	479 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	6.00 kJ/m ²	2.86 ft-lb/in ²	80*10*4; ISO 180/1A
	6.00 kJ/m ² @Temperature -30.0 ^o C	2.86 ft-lb/in ² @Temperature -22.0 ^o F	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	NB	NB	80*10*4; ISO 180/1U
	NB @Temperature -30.0 ^o C	NB @Temperature -22.0 ^o F	80*10*4; ISO 180/1U

Mechanical Properties	Metric	English	Comments
Charpy Impact, Notched	0.400 J/cm ²	1.90 ft-lb/in ²	Edgew 80*10*4 sp=62mm; ISO 179/1eA
	1.00 J/cm ²	4.76 ft-lb/in ²	ISO 179/2C
	0.400 J/cm ² @Temperature -30.0 °C	1.90 ft-lb/in ² @Temperature -22.0 °F	Edgew 80*10*4 sp=62mm; ISO 179/1eA
Taber Abrasion, mg/1000 Cycles	10	10	CS-17, 1 kg; SABIC Method

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	50.0 Åµm/m-Å°C	27.8 Åµin/in-Å°F	ISO 11359-2
	@Temperature 23.0 - 150 Å°C	@Temperature 73.4 - 302 Å°F	
	56.0 Åµm/m-Å°C	31.1 Åµin/in-Å°F	ISO 11359-2
	@Temperature 23.0 - 80.0 Å°C	@Temperature 73.4 - 176 Å°F	
CTE, linear, Transverse to Flow	50.0 Åµm/m-Å°C	27.8 Åµin/in-Å°F	ISO 11359-2
	@Temperature 23.0 - 150 Å°C	@Temperature 73.4 - 302 Å°F	
	56.0 Åµm/m-Å°C	31.1 Åµin/in-Å°F	ISO 11359-2
	@Temperature 23.0 - 80.0 Å°C	@Temperature 73.4 - 176 Å°F	
Thermal Conductivity	0.240 W/m-K	1.67 BTU-in/hr-ftÅ²- Å°F	ISO 8302
Deflection Temperature at 0.46 MPa (66 psi)	200 Å°C	392 Å°F	Edgew 120*10*4 sp=100mm; ISO 75/Be
Deflection Temperature at 1.8 MPa (264 psi)	190 Å°C	374 Å°F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
Vicat Softening Point	211 Å°C	412 Å°F	Rate B/50; ISO 306
	212 Å°C	414 Å°F	Rate B/120; ISO 306
	215 Å°C	419 Å°F	Rate A/50; ISO 306
Glass Transition Temp, Tg	217 Å°C	423 Å°F	
UL RTI, Electrical	170 Å°C	338 Å°F	UL 746B
UL RTI, Mechanical with Impact	170 Å°C	338 Å°F	UL 746B
UL RTI, Mechanical without Impact	170 Å°C	338 Å°F	UL 746B
	V-2	V-2	

Flammability UL 94 Thermal Properties	Metric @Thickness 0.400 mm	English @Thickness 0.0157 in	UL 94 Comments
	V-0 @Thickness 0.750 mm	V-0 @Thickness 0.0295 in	UL 94
	5VA @Thickness 3.00 mm	5VA @Thickness 0.118 in	UL 94
Oxygen Index	47 %	47 %	ISO 4589
Glow Wire Test	960 Â°C @Thickness 3.20 mm	1760 Â°F @Thickness 0.126 in	IEC 60695-2-12

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	ROA; IEC 60093
Dielectric Constant	2.9 @Frequency 1.00e+6 Hz	2.9 @Frequency 1.00e+6 Hz	IEC 60250
	2.9 @Frequency 50.0 - 60.0 Hz	2.9 @Frequency 50.0 - 60.0 Hz	IEC 60250
Dielectric Strength	16.0 kV/mm @Thickness 3.20 mm	406 kV/in @Thickness 0.126 in	in oil; IEC 60243-1
	25.0 kV/mm @Thickness 1.60 mm	635 kV/in @Thickness 0.0630 in	in oil; IEC 60243-1
	33.0 kV/mm @Thickness 0.800 mm	838 kV/in @Thickness 0.0315 in	in oil; IEC 60243-1
Dissipation Factor	0.00050 @Frequency 50.0 - 60.0 Hz	0.00050 @Frequency 50.0 - 60.0 Hz	IEC 60250
	0.0025 @Frequency 2.45e+9 Hz	0.0025 @Frequency 2.45e+9 Hz	IEC 60250
	0.0060 @Frequency 1.00e+6 Hz	0.0060 @Frequency 1.00e+6 Hz	IEC 60250

Comparative Tracking Index Electrical Properties	≥ 100 V Metric	≥ 100 V English	IEC 60112 Comments
	150 V	150 V	IEC 60112

Descriptive Properties	Value	Comments
Ball Pressure Test, 125 \AA C +/- 2 \AA C	PASSES	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China