

SABIC Innovative Plastics ULTEM 1010M PEI (Asia Pacific)

Category : Polymer , Thermoplastic , Polyetherimide (PEI)

Material Notes:

Enhanced flow Polyetherimide (Tg 217C) with internal mold release. ECO Conforming.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-ULTEM-1010M-PEI-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.27 g/cc	1.27 g/cc	ASTM D792
Water Absorption	0.25 % @Time 86400 sec	0.25 % @Time 24.0 hour	ASTM D570
Moisture Absorption at Equilibrium	1.25 %	1.25 %	ASTM D570
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	17.8 g/10 min @Load 6.60 kg, Temperature 337 Â°C	17.8 g/10 min @Load 14.6 lb, Temperature 639 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	109	109	ASTM D785
Tensile Strength, Yield	110 MPa	16000 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	60 %	60 %	Type I, 5 mm/min; ASTM D638
Elongation at Yield	7.0 %	7.0 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	3.58 GPa	519 ksi	5 mm/min; ASTM D638
Flexural Yield Strength	165 MPa	23900 psi	2.6 mm/min, 100 mm span; ASTM D790
Flexural Modulus	3.51 GPa	509 ksi	2.6 mm/min, 100 mm span; ASTM D790
Izod Impact, Notched	0.320 J/cm	0.599 ft-lb/in	ASTM D256
	14.95 J/cm @Thickness 3.20 mm	28.01 ft-lb/in @Thickness 0.126 in	ASTM D256
Izod Impact, Unnotched	13.35 J/cm	25.01 ft-lb/in	ASTM D4812
Gardner Impact	33.0 J	24.3 ft-lb	ASTM D3029

Mechanical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	55.8 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature -20.0 - 150 $^\circ\text{C}$	31.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature -4.00 - 302 $^\circ\text{F}$	ASTM E 831
Thermal Conductivity	0.220 W/m-K	1.53 BTU-in/hr-ft $^\circ\text{Å}^2$ - $^\circ\text{F}$	ASTM C177
Deflection Temperature at 0.46 MPa (66 psi)	207 $^\circ\text{C}$ @Thickness 6.40 mm	405 $^\circ\text{F}$ @Thickness 0.252 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	198 $^\circ\text{C}$ @Thickness 6.40 mm	388 $^\circ\text{F}$ @Thickness 0.252 in	unannealed; ASTM D648
Vicat Softening Point	218 $^\circ\text{C}$	424 $^\circ\text{F}$	Rate B/50; ASTM D1525
Glass Transition Temp, Tg	217 $^\circ\text{C}$	423 $^\circ\text{F}$	
Oxygen Index	44 %	44 %	ASTM D2863

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+17 ohm-cm	1.00e+17 ohm-cm	ASTM D257
Dielectric Constant	3.15 @Frequency 1000 Hz	3.15 @Frequency 1000 Hz	ASTM D150
Dielectric Strength	27.9 kV/mm @Thickness 1.60 mm	709 kV/in @Thickness 0.0630 in	in oil; ASTM D149
	32.6 kV/mm @Thickness 1.60 mm	828 kV/in @Thickness 0.0630 in	in air; ASTM D149
Dissipation Factor	0.0013 @Frequency 1000 Hz	0.0013 @Frequency 1000 Hz	ASTM D150
	0.0025 @Frequency 2.45e+9 Hz	0.0025 @Frequency 2.45e+9 Hz	ASTM D150

Descriptive Properties	Value	Comments
NBS Smoke Density, Flaming, Ds 4 min	2	ASTM E 662

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China