

SABIC Innovative Plastics ULTEM 1110F PEI (Asia Pacific)

Category : Polymer , Thermoplastic , Polyetherimide (PEI)

Material Notes:

Enhanced flow Polyetherimide (Tg 217C). ECO Conforming, UL94 V0 and 5VA listing. US FDA and EU Food Contact compliant, NSF 51 listing. Effective June 2007, this grade will no longer be supported with biocompatibility information and should not be used for medical applications which require biocompatibility. Alternative grade HU1110.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-ULTEM-1110F-PEI-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.36 g/cc	1.36 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	16 g/10 min @Load 6.60 kg, Temperature 337 Â°C	16 g/10 min @Load 14.6 lb, Temperature 639 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	110 MPa	16000 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	70 %	70 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	3.72 GPa	540 ksi	5 mm/min; ASTM D638
Flexural Yield Strength	165 MPa	23900 psi	2.6 mm/min, 100 mm span; ASTM D790
Flexural Modulus	3.72 GPa	540 ksi	2.6 mm/min, 100 mm span; ASTM D790
Izod Impact, Notched	19.22 J/cm @Thickness 3.20 mm	36.01 ft-lb/in @Thickness 0.126 in	ASTM D256
Gardner Impact	23.0 J	17.0 ft-lb	ASTM D3029

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	198 Â°C @Thickness 6.40 mm	388 Â°F @Thickness 0.252 in	unannealed; ASTM D648
Glass Transition Temp, Tg	217 Â°C	423 Â°F	
UL RTI, Electrical	170 Â°C	338 Â°F	UL 746B

UL RTI, Mechanical with Impact Thermal Properties	170 Å°C Metric	338 Å°F English	UL 746B Comments
UL RTI, Mechanical without Impact	170 Å°C	338 Å°F	UL 746B
Flammability, UL94	V-0	V-0	UL 94
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	5VA	5VA	UL 94
	@Thickness 3.00 mm	@Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Arc Resistance	120 - 180 sec	120 - 180 sec	Tungsten; ASTM D495
Comparative Tracking Index	100 - 175 V	100 - 175 V	UL 746A
Hot Wire Ignition, HWI	60 - 120 sec	60 - 120 sec	UL 746A
High Amp Arc Ignition, HAI	15 - 30 arcs	15 - 30 arcs	UL 746A
High Voltage Arc-Tracking Rate, HVTR	25.4 - 80.0 mm/min	1.00 - 3.15 in/min	UL 746A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China