

SABIC Innovative Plastics ULTEM ATX200 PEI Blend (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polyetherimide (PEI)

Material Notes:

High flow Polyetherimide blend. RoHS compliant, UL94 V0 Listing.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-ULTEM-ATX200-PEI-Blend-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.26 g/cc	1.26 g/cc	ASTM D792
Density	1.26 g/cc	0.0455 lb/in ³	ISO 1183
Moisture Absorption	0.500 %	0.500 %	23Â°C / 50% RH; ISO 62
Water Absorption at Saturation	0.90 %	0.90 %	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	on Tensile Bar; SABIC Method
	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	24 g/10 min @Load 6.60 kg, Temperature 337 Â°C	24 g/10 min @Load 14.6 lb, Temperature 639 Â°F	ASTM D1238
Melt Index of Compound	16 g/10 min @Load 5.00 kg, Temperature 340 Â°C	16 g/10 min @Load 11.0 lb, Temperature 644 Â°F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, H358/30	125 MPa	18100 psi	ISO 2039-1
Tensile Strength at Break	75.0 MPa	10900 psi	50 mm/min; ISO 527
	85.0 MPa	12300 psi	Type I, 5 mm/min; ASTM D638
Tensile Strength, Yield	95.0 MPa	13800 psi	50 mm/min; ISO 527
	97.0 MPa	14100 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	20 %	20 %	50 mm/min; ISO 527
	70 %	70 %	Type I, 5 mm/min; ASTM D638

Mechanical Properties	Metric	English	Comments
Elongation at Yield	0.9 %	0.9 %	50 mm/min; ISO 527
	7.0 %	7.0 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	3.00 GPa	435 ksi	1 mm/min; ISO 527
	3.30 GPa	479 ksi	5 mm/min; ASTM D638
Flexural Yield Strength	125 MPa	18100 psi	2 mm/min; ISO 178
	145 MPa	21000 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	3.10 GPa	450 ksi	2 mm/min; ISO 178
	3.17 GPa	460 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	0.530 J/cm	0.993 ft-lb/in	ASTM D256
	0.550 J/cm	1.03 ft-lb/in	
	@Temperature -30.0 °C	@Temperature -22.0 °F	ASTM D256
	26.7 J/cm	50.0 ft-lb/in	
	@Thickness 3.20 mm	@Thickness 0.126 in	ASTM D256
Izod Impact, Unnotched	20.83 J/cm	39.02 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	5.00 kJ/mÂ²	2.38 ft-lb/inÂ²	80*10*4; ISO 180/1A
	5.00 kJ/mÂ²	2.38 ft-lb/inÂ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	80*10*4; ISO 180/1A
Charpy Impact, Notched	0.400 J/cmÂ²	1.90 ft-lb/inÂ²	Edgew 80*10*4 sp=62mm; ISO 179/1eA
	0.400 J/cmÂ²	1.90 ft-lb/inÂ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	Edgew 80*10*4 sp=62mm; ISO 179/1eA
Dart Drop, Total Energy	50.0 J	36.9 ft-lb	
	@Temperature 23.0 °C	@Temperature 73.4 °F	ASTM D3763
Taber Abrasion, mg/1000 Cycles	20	20	CS-17, 1 kg; SABIC Method

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	50.0 Âµm/m-Â°C	27.8 Âµin/in-Â°F	
	@Temperature -40.0 -	@Temperature -40.0 -	ASTM E 831

Thermal Properties	150 Â°C Metric	302 Â°F English	Comments
	50.0 Âµm/m-Â°C	27.8 Âµin/in-Â°F	
	@Temperature 23.0 - 150 Â°C	@Temperature 73.4 - 302 Â°F	ISO 11359-2
CTE, linear, Transverse to Flow	50.0 Âµm/m-Â°C	27.8 Âµin/in-Â°F	
	@Temperature -40.0 - 150 Â°C	@Temperature -40.0 - 302 Â°F	ASTM E 831
	50.0 Âµm/m-Â°C	27.8 Âµin/in-Â°F	
	@Temperature 23.0 - 150 Â°C	@Temperature 73.4 - 302 Â°F	ISO 11359-2
Thermal Conductivity	0.230 W/m-K	1.60 BTU-in/hr-ftÂ²-Â°F	ISO 8302
Deflection Temperature at 0.46 MPa (66 psi)	195 Â°C	383 Â°F	Edgew 120*10*4 sp=100mm; ISO 75/Be
Deflection Temperature at 1.8 MPa (264 psi)	180 Â°C	356 Â°F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
	187 Â°C	369 Â°F	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D648
	191 Â°C	376 Â°F	
	@Thickness 6.40 mm	@Thickness 0.252 in	unannealed; ASTM D648
Vicat Softening Point	200 Â°C	392 Â°F	Rate B/50; ISO 306
	205 Â°C	401 Â°F	Rate B/120; ISO 306
	209 Â°C	408 Â°F	Rate B/50; ASTM D1525
	210 Â°C	410 Â°F	Rate A/50; ISO 306
Flammability, UL94	V-2	V-2	
	@Thickness 0.750 mm	@Thickness 0.0295 in	UL 94
	V-0	V-0	
	@Thickness 1.50 mm	@Thickness 0.0591 in	UL 94

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	ROA; IEC 60093
Dielectric Constant	2.9	2.9	
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	IEC 60250

Electrical Properties	Metric	English	Comments
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	IEC 60250
Dissipation Factor	0.0010	0.0010	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
	0.0050	0.0050	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	IEC 60250
Comparative Tracking Index	150 V	150 V	IEC 60112
Hot Wire Ignition, HWI	>= 120 sec	>= 120 sec	UL 746A
High Amp Arc Ignition, HAI	0.00 - 15 arcs	0.00 - 15 arcs	UL 746A

Descriptive Properties	Value	Comments
Ball Pressure Test, 125Â°C +/- 2Â°C	PASSES	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China