

## SABIC Innovative Plastics ULTEM SF2350 PEI Blend

Category : Polymer , Thermoplastic , Polyetherimide (PEI)

### Material Notes:

High flow Ultem blends for thin wall application

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-ULTEM-SF2350-PEI-Blend.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-ULTEM-SF2350-PEI-Blend.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.52 g/cc	1.52 g/cc	ASTM D792
Density	1.52 g/cc	0.0549 lb/in <sup>3</sup>	ISO 1183
Melt Flow	14.7 g/10 min	14.7 g/10 min	ASTM D1238
	@Load 6.60 kg, Temperature 337 Â°C	@Load 14.6 lb, Temperature 639 Â°F	
Melt Index of Compound	30 g/10 min	30 g/10 min	MVR [cm <sup>3</sup> /10 min]; ISO 1133
	@Load 10.0 kg, Temperature 345 Â°C	@Load 22.0 lb, Temperature 653 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	171 MPa	24800 psi	5 mm/min; ISO 527
	172 MPa	24900 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	2.5 %	2.5 %	5 mm/min; ISO 527
	2.6 %	2.6 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	11.6 GPa	1680 ksi	5 mm/min; ASTM D638
Flexural Yield Strength	222 MPa	32200 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	9.32 GPa	1350 ksi	1.3 mm/min, 50 mm span; ASTM D790
	9.40 GPa	1360 ksi	2 mm/min; ISO 178
Izod Impact, Notched	0.950 J/cm	1.78 ft-lb/in	ASTM D256
Izod Impact, Notched (ISO)	10.0 kJ/m <sup>2</sup>	4.76 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	14.0 Âµm/m-Â°C	7.78 Âµin/in-Â°F	ISO 11359-2
	@Temperature 23.0 - 150 Â°C	@Temperature 73.4 - 302 Â°F	

Thermal Properties	Metric µm/m-°C	English µin/in-°F	Comments
	@Temperature -40.0 - 150 °C	@Temperature -40.0 - 302 °F	ASTM E 831
CTE, linear, Transverse to Flow	55.0 µm/m-°C	30.6 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 150 °C	@Temperature -40.0 - 302 °F	
Deflection Temperature at 1.8 MPa (264 psi)	56.0 µm/m-°C	31.1 µin/in-°F	ISO 11359-2
	@Temperature 23.0 - 150 °C	@Temperature 73.4 - 302 °F	
Deflection Temperature at 1.8 MPa (264 psi)	209 °C	408 °F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
	204 °C	399 °F	unannealed; ASTM D648
Flammability, UL94	@Thickness 3.20 mm	@Thickness 0.126 in	UL 94 by SABIC-IP
	V-0	V-0	
	@Thickness 1.50 mm	@Thickness 0.0591 in	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China