

SABIC Innovative Plastics Ultem 2212 PEI (Asia Pacific)

Category : Polymer , Thermoplastic , Polyetherimide (PEI)

Material Notes:

20% Milled glass filled, enhanced flow Polyetherimide (Tg 217C). ECO Conforming, UL94 V0 and 5VA listing. This data was supplied by SABIC-IP for the Asia Pacific region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Ultem-2212-PEI-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.43 g/cc	1.43 g/cc	ASTM D 792
Melt Flow	13.2 g/10 min	13.2 g/10 min	ASTM D 1238
	@Load 6.60 kg, Temperature 337 Â°C	@Load 14.6 lb, Temperature 639 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	92.0 MPa	13300 psi	Type I, 5 mm/min; ASTM D 638
Elongation at Break	6.0 %	6.0 %	Type I, 5 mm/min; ASTM D 638
Tensile Modulus	4.27 GPa	619 ksi	5 mm/min; ASTM D 638
Flexural Strength	172 MPa	24900 psi	2.6 mm/min, 100 mm span; ASTM D 790
Flexural Modulus	5.10 GPa	740 ksi	2.6 mm/min, 100 mm span; ASTM D 790
Izod Impact, Notched	0.480 J/cm	0.899 ft-lb/in	ASTM D 256
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
	3.84 J/cm	7.19 ft-lb/in	reverse notched; ASTM D 256
	@Thickness 3.20 mm	@Thickness 0.126 in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	205 Â°C	401 Â°F	unannealed; ASTM D 648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Glass Transition Temp, Tg	217 Â°C	423 Â°F	
UL RTI, Electrical	170 Â°C	338 Â°F	UL 746B
UL RTI, Mechanical with Impact	170 Â°C	338 Â°F	UL 746B
UL RTI, Mechanical without Impact	170 Â°C	338 Â°F	UL 746B

Thermal Properties	Metric	English	Comments
Flammability, UL94	@Thickness 0.400 mm	@Thickness 0.0157 in	UL 94

Electrical Properties	Metric	English	Comments
Arc Resistance	0.00 - 60 sec	0.00 - 60 sec	Tungsten, PLC code 7; ASTM D 495
Comparative Tracking Index	100 - 175 V	100 - 175 V	PLC code 4; UL 746A
Hot Wire Ignition, HWI	60 - 120 sec	60 - 120 sec	PLC code 1; UL 746A
High Amp Arc Ignition, HAI	15 - 30 arcs	15 - 30 arcs	surface, PLC code 3; UL 746A
High Voltage Arc-Tracking Rate, HVTR	25.4 - 80.0 mm/min	1.00 - 3.15 in/min	PLC code 2; UL 746A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China