

## SABIC Innovative Plastics Valox® 325 PBT (Asia Pacific)

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT)

### Material Notes:

General purpose, unreinforced, improved processing. Applications like sprinklers and nozzles, pumps, door handle, tank covers, pens, pencils etc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-Valox-325-PBT-Asia-Pacific.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Valox-325-PBT-Asia-Pacific.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.31 g/cc	1.31 g/cc	ASTM D792
Water Absorption	0.080 % @Time 86400 sec	0.080 % @Time 24.0 hour	ASTM D570
Moisture Absorption at Equilibrium	0.34 %	0.34 %	ASTM D570
Linear Mold Shrinkage, Flow	0.0090 - 0.016 cm/cm @Thickness 0.750 - 2.30 mm	0.0090 - 0.016 in/in @Thickness 0.0295 - 0.0906 in	SABIC Method
	0.015 - 0.023 cm/cm @Thickness 2.30 - 4.60 mm	0.015 - 0.023 in/in @Thickness 0.0906 - 0.181 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.010 - 0.017 cm/cm @Thickness 0.750 - 2.30 mm	0.010 - 0.017 in/in @Thickness 0.0295 - 0.0906 in	SABIC Method
	0.016 - 0.024 cm/cm @Thickness 2.30 - 4.60 mm	0.016 - 0.024 in/in @Thickness 0.0906 - 0.181 in	SABIC Method

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	117	117	ASTM D785
Tensile Strength, Yield	51.0 MPa	7400 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	200 %	200 %	Type I, 50 mm/min; ASTM D638
Flexural Yield Strength	82.0 MPa	11900 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.34 GPa	339 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	0.530 J/cm	0.993 ft-lb/in	ASTM D256

Izod Impact, Unnotched Mechanical Properties	16.02 J/cm Metric	30.01 ft-lb/in English	ASTM D4812 Comments
Gardner Impact	40.0 J	29.5 ft-lb	ASTM D3029

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	81.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	45.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM E 831
	@Temperature -40.0 - 40.0 $\text{Å}^\circ\text{C}$	@Temperature -40.0 - 104 $\text{Å}^\circ\text{F}$	
Deflection Temperature at 0.46 MPa (66 psi)	139 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	77.2 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM E 831
	@Temperature 60.0 - 138 $\text{Å}^\circ\text{C}$	@Temperature 140 - 280 $\text{Å}^\circ\text{F}$	
Deflection Temperature at 1.8 MPa (264 psi)	154 $\text{Å}^\circ\text{C}$	309 $\text{Å}^\circ\text{F}$	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
UL RTI, Electrical	54.0 $\text{Å}^\circ\text{C}$	129 $\text{Å}^\circ\text{F}$	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
UL RTI, Mechanical with Impact	120 $\text{Å}^\circ\text{C}$	248 $\text{Å}^\circ\text{F}$	UL 746B
UL RTI, Mechanical without Impact	140 $\text{Å}^\circ\text{C}$	284 $\text{Å}^\circ\text{F}$	UL 746B
Flammability, UL94	HB	HB	UL 94
	@Thickness 0.830 mm	@Thickness 0.0327 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	$\geq 4.00\text{e}+16$ ohm-cm	$\geq 4.00\text{e}+16$ ohm-cm	ASTM D257
Dielectric Constant	3.1	3.1	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dielectric Strength	3.3	3.3	ASTM D150
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	15.7 kV/mm	399 kV/in	in air; ASTM D149
	@Thickness 3.20 mm	@Thickness 0.126 in	
Dielectric Strength	15.7 kV/mm	399 kV/in	in oil; ASTM D149
	@Thickness 3.20 mm	@Thickness 0.126 in	
Dielectric Strength	23.2 kV/mm	589 kV/in	in oil; ASTM D149
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Dissipation Factor			ASTM D150
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.020	0.020	
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	ASTM D150
Arc Resistance	180 - 240 sec	180 - 240 sec	Tungsten; ASTM D495
Comparative Tracking Index	>= 600 V	>= 600 V	UL 746A
Hot Wire Ignition, HWI	15 - 30 sec	15 - 30 sec	UL 746A
High Amp Arc Ignition, HAI	>= 120 arcs	>= 120 arcs	UL 746A
High Voltage Arc-Tracking Rate, HVTR	10.0 - 25.4 mm/min	0.394 - 1.00 in/min	UL 746A

Descriptive Properties	Value	Comments
Specific Volume	0.76cm <sup>3</sup> /g	ASTM D792
UV-light, water exposure/immersion	F1	UL 746C

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China