

SABIC Innovative Plastics Valox[®] 507 PBT+PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/Polybutylene Terephthalate (PBT) Blend, Unreinforced , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

This data was supplied by SABIC-IP for the Asia Pacific region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Valox-507-PBTPC-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.51 g/cc	1.51 g/cc	ASTM D 792
Water Absorption	0.060 %	0.060 %	ASTM D 570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0010 - 0.0020 cm/cm	0.0010 - 0.0020 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	
	0.0030 - 0.0060 cm/cm	0.0030 - 0.0060 in/in	SABIC Method
	@Thickness 6.40 mm	@Thickness 0.252 in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	119	119	ASTM D 785
Tensile Strength, Yield	122 MPa	17700 psi	SABIC - Japan Method
Elongation at Break	3.0 %	3.0 %	SABIC - Japan Method
Flexural Strength	183 MPa	26500 psi	ASTM D 790
Flexural Modulus	8.11 GPa	1180 ksi	ASTM D 790
Izod Impact, Notched	0.880 J/cm	1.65 ft-lb/in	ASTM D 256
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	

Thermal Properties	Metric	English	Comments
CTE, linear	30.0 Âµm/m-Â°C	16.7 Âµin/in-Â°F	TMA
	@Temperature -30.0 - 30.0 Â°C	@Temperature -22.0 - 86.0 Â°F	
Deflection Temperature at 0.46 MPa (66 psi)	201 Â°C	394 Â°F	unannealed; ASTM D 648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa	216 Â°C	421 Â°F	unannealed; ASTM D 648

Thermal Properties	Metric	English	Comments
	@ Thickness 3.20 mm	@ Thickness 0.126 in	
Flammability, UL94	HB	HB	UL 94
	@ Thickness 0.830 mm	@ Thickness 0.0327 in	

Electrical Properties	Metric	English	Comments
Surface Resistance	1.00e+16 ohm	1.00e+16 ohm	ASTM D 257
Arc Resistance	60 - 120 sec	60 - 120 sec	Tungsten, PLC code 6; ASTM D 495

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China