

SABIC Innovative Plastics Valox® AB9515 ABS+PBT (Asia Pacific)

Category : Polymer , Thermoplastic , ABS Polymer , ABS/Polyester Alloy , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

This data was supplied by SABIC-IP for the Asia Pacific region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Valox-AB9515-ABSPBT-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.45 g/cc	1.45 g/cc	ASTM D 792
Water Absorption	0.060 % @Time 86400 sec	0.060 % @Time 24.0 hour	ASTM D 570
Linear Mold Shrinkage, Flow	0.0020 - 0.0070 cm/cm @Thickness 3.20 mm	0.0020 - 0.0070 in/in @Thickness 0.126 in	SABIC Method

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	94.0 MPa	13600 psi	SABIC - Japan Method
Elongation at Break	8.0 %	8.0 %	SABIC - Japan Method
Flexural Strength	125 MPa	18100 psi	ASTM D 790
Flexural Modulus	5.40 GPa	783 ksi	ASTM D 790
Izod Impact, Notched	0.490 J/cm @Temperature 23.0 Â°C	0.918 ft-lb/in @Temperature 73.4 Â°F	ASTM D 256

Thermal Properties	Metric	English	Comments
CTE, linear	50.0 Âµm/m-Â°C @Temperature -30.0 - 30.0 Â°C	27.8 Âµin/in-Â°F @Temperature -22.0 - 86.0 Â°F	TMA
Deflection Temperature at 0.46 MPa (66 psi)	180 Â°C @Thickness 3.20 mm	356 Â°F @Thickness 0.126 in	unannealed; ASTM D 648
Deflection Temperature at 1.8 MPa (264 psi)	214 Â°C @Thickness 3.20 mm	417 Â°F @Thickness 0.126 in	unannealed; ASTM D 648
Flammability, UL94	V-0 @Thickness 0.750 mm	V-0 @Thickness 0.0295 in	UL 94

Electrical Properties	Metric	English	Comments
Surface Resistance	1.00e+16 ohm	1.00e+16 ohm	ASTM D 257
Dielectric Constant	3.7	3.7	ASTM D 150
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China