

SABIC Innovative Plastics Valox[®] HR426 PBT (Asia Pacific)

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

AUTOMOTIVE. 30% GR, hydrolytically stable PBT. Excellent strength, stiffness and dimensional stability.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Valox-HR426-PBT-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.53 g/cc	1.53 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0030 - 0.0050 cm/cm	0.0030 - 0.0050 in/in	SABIC Method
	@Thickness 1.50 - 3.20 mm	@Thickness 0.0591 - 0.126 in	
Linear Mold Shrinkage, Transverse	0.0050 - 0.0080 cm/cm	0.0050 - 0.0080 in/in	SABIC Method
	@Thickness 3.20 - 4.60 mm	@Thickness 0.126 - 0.181 in	
Linear Mold Shrinkage, Transverse	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	SABIC Method
	@Thickness 1.50 - 3.20 mm	@Thickness 0.0591 - 0.126 in	
Linear Mold Shrinkage, Transverse	0.0060 - 0.0090 cm/cm	0.0060 - 0.0090 in/in	SABIC Method
	@Thickness 3.20 - 4.60 mm	@Thickness 0.126 - 0.181 in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength at Break	117 MPa	17000 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	3.0 %	3.0 %	Type I, 5 mm/min; ASTM D638
Flexural Modulus	6.89 GPa	999 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	0.900 J/cm	1.69 ft-lb/in	ASTM D256
Izod Impact, Unnotched	8.01 J/cm	15.0 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	218 Â°C	424 Â°F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Deflection Temperature at 1.8 MPa (264 psi)	207 Â°C	405 Â°F	unannealed; ASTM D648

Thermal Properties	@Thickness 6.40 mm Metric	@Thickness 0.252 in English	Comments
UL RTI, Electrical	140 Â°C	284 Â°F	UL 746B
UL RTI, Mechanical with Impact	140 Â°C	284 Â°F	UL 746B
UL RTI, Mechanical without Impact	140 Â°C	284 Â°F	UL 746B
Flammability, UL94	HB @Thickness 0.760 mm	HB @Thickness 0.0299 in	UL 94

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.90e+16 ohm-cm	1.90e+16 ohm-cm	ASTM D257
Dielectric Constant	3.13	3.13	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dielectric Strength	3.24	3.24	ASTM D150
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Dielectric Strength	19.1 kV/mm	485 kV/in	in oil; ASTM D149
	@Thickness 3.20 mm	@Thickness 0.126 in	
Dissipation Factor	0.0030	0.0030	ASTM D150
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Dissipation Factor	0.014	0.014	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Arc Resistance	120 - 180 sec	120 - 180 sec	Tungsten; ASTM D495
Comparative Tracking Index	400 - 600 V	400 - 600 V	UL 746A
Hot Wire Ignition, HWI	>= 120 sec	>= 120 sec	UL 746A
High Amp Arc Ignition, HAI	15 - 30 arcs	15 - 30 arcs	UL 746A
High Voltage Arc-Tracking Rate, HVTR	25.4 - 80.0 mm/min	1.00 - 3.15 in/min	UL 746A

Descriptive Properties	Value	Comments
50% Loss of TS at 120Â°C/100% RH	0days	SABIC Method
50% Loss of TS at 85Â°C/94% RH	200Days (>)	SABIC Method
Specific Volume	0.65cm ³ /g	ASTM D792

Descriptive Properties	Value	Comments
------------------------	-------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China