

## SABIC Innovative Plastics Valox® IQ357M PBT+PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/Polybutylene Terephthalate (PBT) Blend, Unreinforced , Polyester, TP , Polybutylene Terephthalate (PBT)

### Material Notes:

Valox\* Resin IQ357M: Environmentally responsible, low carbon footprint iQ\* PBT + PC alloy. UL94 V-0 @0.63 mm. Impact modified, easy flow product with mold release.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-Valox-IQ357M-PBTPC-Asia-Pacific.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Valox-IQ357M-PBTPC-Asia-Pacific.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.35 g/cc	1.35 g/cc	ASTM D792
Density	1.34 g/cc	0.0484 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption	0.0800 %	0.0800 %	23 <sup>o</sup> C / 50% RH; ISO 62
Water Absorption at Saturation	0.080 %	0.080 %	ISO 62
Linear Mold Shrinkage, Flow	0.011 - 0.014 cm/cm @Thickness 3.20 mm	0.011 - 0.014 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	9.3 g/10 min @Load 5.00 kg, Temperature 250 <sup>o</sup> C	9.3 g/10 min @Load 11.0 lb, Temperature 482 <sup>o</sup> F	ASTM D1238
Melt Index of Compound	7.0 g/10 min @Load 5.00 kg, Temperature 250 <sup>o</sup> C	7.0 g/10 min @Load 11.0 lb, Temperature 482 <sup>o</sup> F	MVR [cm <sup>3</sup> /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	40.0 MPa	5800 psi	50 mm/min; ISO 527
	41.0 MPa	5950 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	48.0 MPa	6960 psi	Type I, 50 mm/min; ASTM D638
	48.0 MPa	6960 psi	50 mm/min; ISO 527
Elongation at Break	74 %	74 %	Type I, 50 mm/min; ASTM D638
	74.8 %	74.8 %	50 mm/min; ISO 527
Elongation at Yield	4.6 %	4.6 %	50 mm/min; ISO 527
	4.9 %	4.9 %	Type I, 50 mm/min; ASTM D638
Tensile Modulus	2.00 GPa	290 ksi	5 mm/min; ASTM D638

Mechanical Properties	Metric <sup>°Pa</sup>	English	Comments <sup>ISO 527</sup>
Flexural Yield Strength	73.0 MPa	10600 psi	2 mm/min; ISO 178
	75.0 MPa	10900 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.05 GPa	297 ksi	2 mm/min; ISO 178
	2.10 GPa	305 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	4.90 J/cm	9.18 ft-lb/in	ASTM D256
	1.67 J/cm @Temperature -30.0 °C	3.13 ft-lb/in @Temperature -22.0 °F	ASTM D256
Izod Impact, Notched (ISO)	31.0 kJ/m <sup>2</sup>	14.8 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A
	10.0 kJ/m <sup>2</sup> @Temperature -30.0 °C	4.76 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	80*10*4; ISO 180/1A
Charpy Impact, Notched	3.40 J/cm <sup>2</sup>	16.2 ft-lb/in <sup>2</sup>	Edgew 80*10*4 sp=62mm; ISO 179/1eA
Dart Drop, Total Energy	50.0 J	36.9 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	81.6 Åµm/m-Å°C	45.3 Åµin/in-Å°F	ASTM E 831
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
	81.6 Åµm/m-Å°C	45.3 Åµin/in-Å°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
CTE, linear, Transverse to Flow	97.4 Åµm/m-Å°C	54.1 Åµin/in-Å°F	ASTM E 831
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
Deflection Temperature at 0.46 MPa (66 psi)	127 Å°C	261 Å°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	

Thermal Properties <small>(Deflection Temperature at 1.8 MPa 1.8 MPa)</small>	84.0 Â°C Metric	183 Â°F English	Flatw 80x10x4 sp=64mm; ISO 75/Af Comments
	88.0 Â°C @Thickness 3.20 mm	190 Â°F @Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	130 Â°C	266 Â°F	Rate B/50; ASTM D1525
	130 Â°C	266 Â°F	Rate B/50; ISO 306
	133 Â°C	271 Â°F	Rate B/120; ISO 306
UL RTI, Electrical	120 Â°C	248 Â°F	UL 746B
UL RTI, Mechanical with Impact	120 Â°C	248 Â°F	UL 746B
UL RTI, Mechanical without Impact	140 Â°C	284 Â°F	UL 746B
Flammability, UL94	V-0 @Thickness 0.630 mm	V-0 @Thickness 0.0248 in	UL 94 by SABIC-IP
	5VA @Thickness 3.00 mm	5VA @Thickness 0.118 in	UL 94 by SABIC-IP

Electrical Properties	Metric	English	Comments
Arc Resistance	60 - 120 sec	60 - 120 sec	UL 746A
Comparative Tracking Index	250 - 400 V	250 - 400 V	UL 746A
Hot Wire Ignition, HWI	30 - 60 sec	30 - 60 sec	UL 746A
High Amp Arc Ignition, HAI	15 - 30 arcs	15 - 30 arcs	UL 746A
High Voltage Arc-Tracking Rate, HVTR	>= 150 mm/min	>= 5.91 in/min	UL 746A

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China