

SABIC Innovative Plastics Valox® V9260CS PET (Asia Pacific)

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET)

Material Notes:

Color Stable Glass filled PET

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Valox-V9260CS-PET-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Density	1.56 g/cc	0.0564 lb/in ³	ISO 1183
Moisture Absorption	0.0700 %	0.0700 %	23 ^o C / 50% RH; ISO 62
Water Absorption at Saturation	0.27 %	0.27 %	ISO 62
Linear Mold Shrinkage, Flow	0.0020 - 0.0050 cm/cm @Thickness 3.20 mm	0.0020 - 0.0050 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0050 - 0.0080 cm/cm @Thickness 3.20 mm	0.0050 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Melt Index of Compound	14 g/10 min @Load 2.16 kg, Temperature 265 ^o C	14 g/10 min @Load 4.76 lb, Temperature 509 ^o F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	155 MPa	22500 psi	5 mm/min; ISO 527
Tensile Strength, Yield	155 MPa	22500 psi	5 mm/min; ISO 527
Elongation at Break	2.0 %	2.0 %	5 mm/min; ISO 527
Elongation at Yield	2.0 %	2.0 %	5 mm/min; ISO 527
Tensile Modulus	9.60 GPa	1390 ksi	1 mm/min; ISO 527
Flexural Yield Strength	210 MPa	30500 psi	2 mm/min; ISO 178
Flexural Modulus	9.10 GPa	1320 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	6.00 kJ/m ²	2.86 ft-lb/in ²	80*10*4; ISO 180/1A
	6.00 kJ/m ² @Temperature -30.0 ^o C	2.86 ft-lb/in ² @Temperature -22.0 ^o F	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	40.0 kJ/m ²	19.0 ft-lb/in ²	80*10*4; ISO 180/1U

Mechanical Properties	Metric	English	Comments
	35.0 kJ/m ² @Temperature -30.0 Â°C	16.7 ft-lb/in ² @Temperature -22.0 Â°F	80*10*4, ISO 180/1U
Charpy Impact, Notched	0.600 J/cm ²	2.86 ft-lb/in ²	Edgew 80*10*4 sp=62mm; ISO 179/1eA

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	25.0 Âµm/m-Â°C @Temperature 23.0 - 80.0 Â°C	13.9 Âµin/in-Â°F @Temperature 73.4 - 176 Â°F	ISO 11359-2
CTE, linear, Transverse to Flow	100 Âµm/m-Â°C @Temperature 23.0 - 80.0 Â°C	55.6 Âµin/in-Â°F @Temperature 73.4 - 176 Â°F	ISO 11359-2
Deflection Temperature at 1.8 MPa (264 psi)	230 Â°C	446 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/ Af
Vicat Softening Point	230 Â°C	446 Â°F	Rate B/50; ISO 306
	235 Â°C	455 Â°F	Rate B/120; ISO 306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China