

SABIC Innovative Plastics XYLEX X7509HP PC+POLYESTER (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/PET Polyester Blend , Polyester, TP , Polyethylene Terephthalate (PET)

Material Notes:

PC+Polyester alloy. Houseware applications. USA/Europe Food contact. this grade will no longer be supported with biocompatibility information and should not be used for medical applications which require biocompatibility. Alternative grade HX7509HP.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-XYLEX-X7509HP-PCPOLYESTER-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183
Moisture Absorption	0.0500 %	0.0500 %	23 ^o C / 50% RH; ISO 62
Water Absorption at Saturation	0.12 %	0.12 %	ISO 62
Linear Mold Shrinkage, Flow	0.0040 - 0.0060 cm/cm @Thickness 3.20 mm	0.0040 - 0.0060 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	12 g/10 min @Load 2.16 kg, Temperature 265 ^o C	12 g/10 min @Load 4.76 lb, Temperature 509 ^o F	ASTM D1238
Melt Index of Compound	11 g/10 min @Load 2.16 kg, Temperature 265 ^o C	11 g/10 min @Load 4.76 lb, Temperature 509 ^o F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	62.0 MPa	8990 psi	50 mm/min; ISO 527
	63.0 MPa	9140 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	60.0 MPa	8700 psi	Type I, 50 mm/min; ASTM D638
	60.0 MPa	8700 psi	50 mm/min; ISO 527
Elongation at Break	133 %	133 %	50 mm/min; ISO 527
	135 %	135 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	5.8 %	5.8 %	50 mm/min; ISO 527

Mechanical Properties	Metric	English	Comments
Tensile Modulus	2.14 GPa	310 ksi	50 mm/min; ASTM D638
	2.30 GPa	334 ksi	1 mm/min; ISO 527
Flexural Strength	92.0 MPa	13300 psi	2 mm/min; ISO 178
Flexural Yield Strength	95.0 MPa	13800 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.25 GPa	326 ksi	2 mm/min; ISO 178
	2.30 GPa	334 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	8.50 J/cm	15.9 ft-lb/in	ASTM D256
	0.700 J/cm	1.31 ft-lb/in	ASTM D256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Izod Impact, Notched (ISO)	9.00 kJ/m ²	4.28 ft-lb/in ²	80*10*4; ISO 180/1A
	8.00 kJ/m ²	3.81 ft-lb/in ²	80*10*4; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	1.00 J/cm ²	4.76 ft-lb/in ²	Edgew 80*10*4 sp=62mm; ISO 179/1eA
Dart Drop, Total Energy	77.0 J	56.8 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	68.0 Åµm/m-Å°C	37.8 Åµin/in-Å°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
	90.0 Åµm/m-Å°C	50.0 Åµin/in-Å°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Å°C	@Temperature 73.4 - 140 Å°F	
	104 Åµm/m-Å°C	57.8 Åµin/in-Å°F	ASTM E 831
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
CTE, linear, Transverse to Flow	68.0 Åµm/m-Å°C	37.8 Åµin/in-Å°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	

Thermal Properties	Metric @Temperature 23.0 - 60.0 °C	English @Temperature 73.4 - 140 °F	Comments ISO 11359-2
	104 µm/m-°C	57.8 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
Deflection Temperature at 0.46 MPa (66 psi)	119 °C @Thickness 3.20 mm	246 °F @Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	106 °C	223 °F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
	108 °C	226 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	106 °C @Thickness 3.20 mm	223 °F @Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	125 °C	257 °F	Rate B/50; ISO 306
	126 °C	259 °F	Rate B/120; ISO 306
	126 °C	259 °F	Rate B/50; ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China