

SABIC Innovative Plastics Xenoy® CL101 PBT+PC (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/Polybutylene Terephthalate (PBT) Blend, Unreinforced , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

Xenoy CL101 is an unfilled, impact modified PC/PBT blend with excellent solvent resistance and low-temperature ductility. It has a proven track record in off-line painted exterior automotive applications. ISO1043: PC+PBT-I.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Xenoy-CL101-PBTPC-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.22 g/cc	1.22 g/cc	ASTM D792
Density	1.22 g/cc	0.0441 lb/in ³	ISO 1183
Moisture Absorption	0.150 %	0.150 %	23Å°C / 50% RH; ISO 62
Water Absorption at Saturation	0.50 %	0.50 %	ISO 62
Linear Mold Shrinkage, Flow	0.0070 - 0.011 cm/cm	0.0070 - 0.011 in/in	on Tensile Bar; SABIC Method
Linear Mold Shrinkage, Transverse	0.0070 - 0.011 cm/cm	0.0070 - 0.011 in/in	on Tensile Bar; SABIC Method
Melt Flow	14 g/10 min @Load 5.00 kg, Temperature 250 Å°C	14 g/10 min @Load 11.0 lb, Temperature 482 Å°F	ASTM D1238
Melt Index of Compound	13 g/10 min @Load 5.00 kg, Temperature 250 Å°C	13 g/10 min @Load 11.0 lb, Temperature 482 Å°F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell L	89	89	ISO 2039-2
Hardness, H358/30	82.0 MPa	11900 psi	ISO 2039-1
Tensile Strength at Break	44.0 MPa	6380 psi	50 mm/min; ISO 527
	49.0 MPa	7110 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	52.0 MPa	7540 psi	50 mm/min; ISO 527
	53.0 MPa	7690 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	50 %	50 %	Type I, 50 mm/min; ASTM D638
	50 %	50 %	50 mm/min; ISO 527

Mechanical Properties	Metric	English	Comments
	4.5 %	4.5 %	50 mm/min; ISO 527
Tensile Modulus	2.05 GPa	297 ksi	50 mm/min; ASTM D638
	2.05 GPa	297 ksi	1 mm/min; ISO 527
Flexural Yield Strength	75.0 MPa	10900 psi	1.3 mm/min, 50 mm span; ASTM D790
	75.0 MPa	10900 psi	2 mm/min; ISO 178
Flexural Modulus	2.00 GPa	290 ksi	1.3 mm/min, 50 mm span; ASTM D790
	2.00 GPa	290 ksi	2 mm/min; ISO 178
Izod Impact, Notched	6.25 J/cm	11.7 ft-lb/in	ASTM D256
	4.50 J/cm	8.43 ft-lb/in	ASTM D256
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
	6.00 J/cm	11.2 ft-lb/in	ASTM D256
	@Temperature 0.000 Â°C	@Temperature 32.0 Â°F	
Izod Impact, Notched (ISO)	50.0 kJ/mÂ²	23.8 ft-lb/inÂ²	80*10*4; ISO 180/1A
	25.0 kJ/mÂ²	11.9 ft-lb/inÂ²	80*10*4; ISO 180/1A
	@Temperature -40.0 Â°C	@Temperature -40.0 Â°F	
	35.0 kJ/mÂ²	16.7 ft-lb/inÂ²	80*10*4; ISO 180/1A
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
Izod Impact, Unnotched (ISO)	NB	NB	80*10*4; ISO 180/1U
	NB	NB	80*10*4; ISO 180/1U
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
Charpy Impact Unnotched	NB	NB	Edgew 80*10*4 sp=62mm; ISO 179/1eU
	NB	NB	Edgew 80*10*4 sp=62mm; ISO 179/1eU
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
Charpy Impact, Notched	3.00 J/cmÂ²	14.3 ft-lb/inÂ²	ISO 179/2C
	5.80 J/cmÂ²	27.6 ft-lb/inÂ²	Edgew 80*10*4 sp=62mm; ISO

Mechanical Properties	Metric	English	179/1eA Comments
	2.00 J/cm ²	9.52 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	ISO 179/2C
	2.50 J/cm ²	11.9 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	Edgew 80*10*4 sp=62mm; ISO 179/1eA
	2.50 J/cm ²	11.9 ft-lb/in ²	
	@Temperature -20.0 °C	@Temperature -4.00 °F	ISO 179/2C
Taber Abrasion, mg/1000 Cycles	30	30	CS-17, 1 kg; SABIC Method

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	90.0 Åµm/m-Å°C	50.0 Åµin/in-Å°F	
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	ASTME 831
	90.0 Åµm/m-Å°C	50.0 Åµin/in-Å°F	
	@Temperature 23.0 - 80.0 Å°C	@Temperature 73.4 - 176 Å°F	ISO 11359-2
CTE, linear, Transverse to Flow	95.0 Åµm/m-Å°C	52.8 Åµin/in-Å°F	
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	ASTME 831
	95.0 Åµm/m-Å°C	52.8 Åµin/in-Å°F	
	@Temperature 23.0 - 80.0 Å°C	@Temperature 73.4 - 176 Å°F	ISO 11359-2
Thermal Conductivity	0.180 W/m-K	1.25 BTU-in/hr-ftÅ²- Å°F	ISO 8302
Deflection Temperature at 0.46 MPa (66 psi)	105 Å°C	221 Å°F	Edgew 120*10*4 sp=100mm; ISO 75/Be
	105 Å°C	221 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
Deflection Temperature at 1.8 MPa (264 psi)	83.0 Å°C	181 Å°F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
	83.0 Å°C	181 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	83.0 Å°C	181 Å°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Vicat Softening Point	120 Å°C	248 Å°F	Rate B/50; ASTM D1525
			Rate B/50; ISO 306

Thermal Properties	120 Â°C Metric	248 Â°F English	Comments
	123 Â°C	253 Â°F	Rate B/120; ISO 306
	155 Â°C	311 Â°F	Rate A/50; ISO 306
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	UL 94 by SABIC-IP

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+14 ohm-cm	>= 1.00e+14 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	ROA; IEC 60093
Dielectric Constant	3.3	3.3	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dielectric Strength	3.3	3.3	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Dielectric Strength	17.0 kV/mm	432 kV/in	in oil; IEC 60243-1
	@Thickness 3.20 mm	@Thickness 0.126 in	
Dielectric Strength	18.0 kV/mm	457 kV/in	short time; IEC 60243-1
	@Thickness 1.00 mm	@Thickness 0.0394 in	
Dissipation Factor	0.0020	0.0020	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Dissipation Factor	0.020	0.020	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	

Descriptive Properties	Value	Comments
Ball Pressure Test, 75Â°C +/- 2Â°C	PASSES	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China