

## SABIC Innovative Plastics Xenoy<sup>®</sup> FXX210SK PBT+PC (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/Polybutylene Terephthalate (PBT) Blend, Unreinforced , Polyester, TP , Polybutylene Terephthalate (PBT)

### Material Notes:

XENOY FXX210SK is an unreinforced PBT+PC injection moulding resin with excellent impact characteristics and containing a metal sparkle Visual FX. Applications: automotive bezels and appliances. XENOY FXX210SK is the visual FX version of XENOY CL100. This data was supplied by SABIC-IP for the Europe-Africa-Middle East region.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-Xenoy-FXX210SK-PBTPC-Europe-Africa-Middle-East.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Xenoy-FXX210SK-PBTPC-Europe-Africa-Middle-East.php)

Physical Properties	Metric	English	Comments
Melt Flow	9.0 g/10 min @Load 2.16 kg, Temperature 250 °C	9.0 g/10 min @Load 4.76 lb, Temperature 482 °F	[cm <sup>3</sup> /10 min] Melt Volume Rate; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	40.0 MPa	5800 psi	50 mm/min; ISO 527
Elongation at Break	60 %	60 %	50 mm/min; ISO 527
Tensile Modulus	2.25 GPa	326 ksi	1 mm/min; ISO 527
Izod Impact, Unnotched (ISO)	32.0 kJ/m <sup>2</sup> @Temperature 23.0 °C	15.2 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
Vicat Softening Point	115 °C	239 °F	Rate B/120; ISO 306

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China