

SABIC Innovative Plastics Xenoy[®] X4820 PBT+PC

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/Polybutylene Terephthalate (PBT) Blend, Unreinforced , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

Xenoy X4820 is a high modulus PC/PBT Blend. This resin provides high chemical resistance, excellent impact, very low creep, low CTE, excellent fatigue and dimensional stability.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Xenoy-X4820-PBTPC.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.25 g/cc	1.25 g/cc	ASTM D792
Density	1.26 g/cc	0.0455 lb/in ³	ISO 1183
Moisture Absorption	0.140 %	0.140 %	23 [°] C / 50% RH; ISO 62
Water Absorption at Saturation	0.42 %	0.42 %	ISO 62
Linear Mold Shrinkage, Flow	0.0095 - 0.011 cm/cm @Thickness 3.20 mm	0.0095 - 0.011 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	10 g/10 min @Load 5.00 kg, Temperature 250 [°] C	10 g/10 min @Load 11.0 lb, Temperature 482 [°] F	ASTM D1238
Melt Index of Compound	12 g/10 min @Load 5.00 kg, Temperature 265 [°] C	12 g/10 min @Load 11.0 lb, Temperature 509 [°] F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	52.0 MPa	7540 psi	50 mm/min; ISO 527
	58.0 MPa	8410 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	57.0 MPa	8270 psi	Type I, 50 mm/min; ASTM D638
	58.0 MPa	8410 psi	50 mm/min; ISO 527
Elongation at Break	100 %	100 %	50 mm/min; ISO 527
	140 %	140 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	4.2 %	4.2 %	Type I, 50 mm/min; ASTM D638
	4.2 %	4.2 %	50 mm/min; ISO 527
Tensile Modulus	3.00 GPa	435 ksi	1 mm/min; ISO 527

Mechanical Properties	Metric ^{°Pa}	English	Comments ^{ASTM D638}
Flexural Yield Strength	87.0 MPa	12600 psi	2 mm/min; ISO 178
	91.0 MPa	13200 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.85 GPa	413 ksi	2 mm/min; ISO 178
	2.90 GPa	421 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	7.00 J/cm	13.1 ft-lb/in	ASTM D256
	1.50 J/cm @Temperature -30.0 °C	2.81 ft-lb/in @Temperature -22.0 °F	ASTM D256
Izod Impact, Notched (ISO)	55.0 kJ/m ²	26.2 ft-lb/in ²	80*10*4; ISO 180/1A
	15.0 kJ/m ² @Temperature -30.0 °C	7.14 ft-lb/in ² @Temperature -22.0 °F	80*10*4; ISO 180/1A
Charpy Impact, Notched	6.00 J/cm ²	28.6 ft-lb/in ²	Edgew 80*10*4 sp=62mm; ISO 179/1eA
Dart Drop, Total Energy	60.0 J @Temperature 23.0 °C	44.3 ft-lb @Temperature 73.4 °F	ASTM D3763

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	75.0 Åµm/m-Å°C	41.7 Åµin/in-Å°F	ASTM E 831
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
	75.0 Åµm/m-Å°C	41.7 Åµin/in-Å°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
CTE, linear, Transverse to Flow	110 Åµm/m-Å°C	61.1 Åµin/in-Å°F	ASTM E 831
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
Deflection Temperature at 1.8 MPa (264 psi)	94.0 Å°C	201 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Åf
	98.0 Å°C	208 Å°F	

Thermal Properties	Metric @ Thickness 3.20 mm	English @ Thickness 0.126 in	unannealed; ASTM D648 Comments
Vicat Softening Point	130 Â°C	266 Â°F	Rate B/50; ASTM D1525
	132 Â°C	270 Â°F	Rate B/50; ISO 306
	134 Â°C	273 Â°F	Rate B/120; ISO 306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China