

## SABIC Innovative Plastics Xenoy® X5600WX PC+POLYESTER (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/PET Polyester Blend , Polyester, TP , Polyethylene Terephthalate (PET)

### Material Notes:

Unreinforced, opaque Polyester+PC alloy. Chemical resistance, dimensional stability and mechanical performance. UV Stabilized. Mold Release  
This data was supplied by SABIC-IP for the Asia Pacific region.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-Xenoy-X5600WX-PCPOLYESTER-Asia-Pacific.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Xenoy-X5600WX-PCPOLYESTER-Asia-Pacific.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	ASTM D 792
Density	1.20 g/cc	0.0434 lb/in <sup>3</sup>	ISO 1183
Linear Mold Shrinkage, Flow	0.0070 - 0.0090 cm/cm @Thickness 3.20 mm	0.0070 - 0.0090 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0070 - 0.0090 cm/cm @Thickness 3.20 mm	0.0070 - 0.0090 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	4.1 g/10 min @Load 5.00 kg, Temperature 250 °C	4.1 g/10 min @Load 11.0 lb, Temperature 482 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	56.0 MPa	8120 psi	50 mm/min; ISO 527
	61.0 MPa	8850 psi	Type I, 50 mm/min; ASTM D 638
Tensile Strength, Yield	55.0 MPa	7980 psi	50 mm/min; ISO 527
	61.0 MPa	8850 psi	Type I, 50 mm/min; ASTM D 638
Elongation at Break	120 %	120 %	Type I, 50 mm/min; ASTM D 638
	120 %	120 %	50 mm/min; ISO 527
Elongation at Yield	4.5 %	4.5 %	50 mm/min; ISO 527
	5.2 %	5.2 %	Type I, 50 mm/min; ASTM D 638
Tensile Modulus	2.48 GPa	360 ksi	50 mm/min; ASTM D 638
Flexural Yield Strength	70.0 MPa	10200 psi	2 mm/min; ISO 178
	99.0 MPa	14400 psi	1.3 mm/min, 50 mm span; ASTM D 790

Flexural Modulus Mechanical Properties	2.15 GPa Metric	312 ksi English	2 mm/min; ISO 178 Comments
	2.48 GPa	360 ksi	1.3 mm/min, 50 mm span; ASTM D 790
Izod Impact, Notched	2.67 J/cm @Temperature -30.0 °C	5.00 ft-lb/in @Temperature -22.0 °F	ASTM D 256
	8.00 J/cm @Temperature 23.0 °C	15.0 ft-lb/in @Temperature 73.4 °F	ASTM D 256
Izod Impact, Notched (ISO)	20.0 kJ/m <sup>2</sup> @Temperature -30.0 °C	9.52 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	80*10*4; ISO 180/1A
	50.0 kJ/m <sup>2</sup> @Temperature 23.0 °C	23.8 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	80*10*4; ISO 180/1A
Charpy Impact, Notched	6.00 J/cm <sup>2</sup> @Temperature 23.0 °C	28.6 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	V-notch Edgew 80*10*4 sp=62mm; ISO 179/1eA
Impact Test	54.0 J @Temperature 23.0 °C	39.8 ft-lb @Temperature 73.4 °F	Instrumented Impact Total Energy; ASTM D 3763

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	69.0 µm/m-°C	38.3 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	69.0 µm/m-°C	38.3 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
CTE, linear, Transverse to Flow	74.0 µm/m-°C	41.1 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	74.0 µm/m-°C	41.1 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
Deflection Temperature at 0.46 MPa (66 psi)	120 °C	248 °F	unannealed; ASTM D 648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	95.0 °C	203 °F	Flatw 80*10*4 sp=64mm; ISO 75/af
	98.0 °C	208 °F	
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D 648

Thermal Properties	Metric	English	Comments
	130 °C	266 °F	Rate B/50; ISO 306
	132 °C	270 °F	Rate B/120; ISO 306

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China