

SABIC Innovative Plastics Xylex X75290Q PC+POLYESTER (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polyester, TP

Material Notes:

PC+ POLYESTER unreinforced alloy developed for optical or lense market. Good flow with good impact and excellent optical quality This data was supplied by SABIC-IP for the Europe-Africa-Middle East region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Xylex-X75290Q-PCPOLYESTER-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D 792
Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.14 %	0.14 %	23 ^o C / 50% RH; ISO 62
Water Absorption at Saturation	0.16 % @Temperature 23.0 ^o C	0.16 % @Temperature 73.4 ^o F	ISO 62
Linear Mold Shrinkage, Flow	0.0040 - 0.0060 cm/cm @Thickness 3.20 mm	0.0040 - 0.0060 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	11 g/10 min @Load 2.16 kg, Temperature 265 ^o C	11 g/10 min @Load 4.76 lb, Temperature 509 ^o F	[cm ³ /10 min] Melt Volume Rate; ISO 1133
	12 g/10 min @Load 2.16 kg, Temperature 265 ^o C	12 g/10 min @Load 4.76 lb, Temperature 509 ^o F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	62.0 MPa	8990 psi	50 mm/min; ISO 527
	63.0 MPa	9140 psi	Type I, 50 mm/min; ASTM D 638
Tensile Strength, Yield	60.0 MPa	8700 psi	Type I, 50 mm/min; ASTM D 638
	60.0 MPa	8700 psi	50 mm/min; ISO 527
Elongation at Break	133 %	133 %	50 mm/min; ISO 527
	135 %	135 %	Type I, 50 mm/min; ASTM D 638
Elongation at Yield	5.8 %	5.8 %	50 mm/min; ISO 527

Mechanical Properties	Metric	English	Type I, 50 mm/min; ASTM D 638 Comments
Tensile Modulus	2.14 GPa	310 ksi	50 mm/min; ASTM D 638
	2.30 GPa	334 ksi	1 mm/min; ISO 527
Flexural Strength	92.0 MPa	13300 psi	2 mm/min; ISO 178
Flexural Yield Strength	95.0 MPa	13800 psi	1.3 mm/min, 50 mm span; ASTM D 790
Flexural Modulus	2.25 GPa	326 ksi	2 mm/min; ISO 178
	2.30 GPa	334 ksi	1.3 mm/min, 50 mm span; ASTM D 790
Izod Impact, Notched	0.100 J/cm	0.187 ft-lb/in	ASTM D 256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	5.20 J/cm	9.74 ft-lb/in	ASTM D 256
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Izod Impact, Notched (ISO)	6.00 kJ/m ²	2.86 ft-lb/in ²	80*10*4; ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	9.00 kJ/m ²	4.28 ft-lb/in ²	80*10*4; ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	1.00 J/cm ²	4.76 ft-lb/in ²	V-notch Edgew 80*10*4 sp=62mm; ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Impact Test	70.0 J	51.6 ft-lb	Instrumented Impact Total Energy; ASTM D 3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	90.0 μm/m-°C	50.0 μin/in-°F	ISO 11359-2
	@Temperature 23.0 - 60.0 °C	@Temperature 73.4 - 140 °F	
	104 μm/m-°C	57.8 μin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
CTE, linear, Transverse to Flow	90.0 μm/m-°C	50.0 μin/in-°F	ISO 11359-2

Thermal Properties	Metric @Temperature 23.0 - 30.0 Â°C	English @Temperature 73.4 - 86.0 Â°F	Comments
	104 Âµm/m-Â°C	57.8 Âµin/in-Â°F	ASTM E 831
	@Temperature -40.0 - 40.0 Â°C	@Temperature -40.0 - 104 Â°F	
Deflection Temperature at 0.46 MPa (66 psi)	119 Â°C	246 Â°F	unannealed; ASTM D 648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	106 Â°C	223 Â°F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
	106 Â°C	223 Â°F	unannealed; ASTM D 648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Vicat Softening Point	124 Â°C	255 Â°F	Rate B/50; ISO 306
	126 Â°C	259 Â°F	Rate B/120; ISO 306
	126 Â°C	259 Â°F	Rate B/50; ASTM D 1525

Optical Properties	Metric	English	Comments
Haze	2.0 %	2.0 %	ASTM D 1003
	@Thickness 2.54 mm	@Thickness 0.100 in	
Transmission, Visible	86 %	86 %	ASTM D 1003
	@Thickness 2.54 mm	@Thickness 0.100 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China