

SCG Chemicals EL-Leneâ,,ç H1000P High Density Polyethylene Pipe Resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Pipe Grade

Material Notes:

Key Characteristics: Good processing, high thermal stability
Recommended Applications: Water pipes, conduit, sewage drainage pipes
Information provided by SCG Chemicals

Order this product through the following link:

http://www.lookpolymers.com/polymer_SCG-Chemicals-EL-Lene-H1000P-High-Density-Polyethylene-Pipe-Resin.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.950 g/cc	0.950 g/cc	ISO 1183
Environmental Stress Crack Resistance	>= 10000 hour	>= 10000 hour	F0; ASTM D1693
Oxidative Induction Time (OIT)	>= 40 min @Temperature 200 Â°C	>= 40 min @Temperature 392 Â°F	ISO/TR10837
Melt Flow	0.22 g/10 min @Load 5.00 kg, Temperature 190 Â°C	0.22 g/10 min @Load 11.0 lb, Temperature 374 Â°F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	64	64	ASTM D2240
Tensile Strength at Break	37.0 MPa	5370 psi	Crosshead speed 100 mm/min; ISO 527
Tensile Strength, Yield	22.0 MPa	3190 psi	Crosshead speed 100 mm/min; ISO 527
Elongation at Break	823 %	823 %	Crosshead speed 100 mm/min; ISO 527
Flexural Modulus	1.00 GPa	145 ksi	ASTM D790
Izod Impact, Notched	3.04 J/cm @Temperature -20.0 Â°C	5.69 ft-lb/in @Temperature -4.00 Â°F	ASTM D256
	3.43 J/cm @Temperature 0.000 Â°C	6.43 ft-lb/in @Temperature 32.0 Â°F	ASTM D256
	3.92 J/cm @Temperature 23.0 Â°C	7.35 ft-lb/in @Temperature 73.4 Â°F	ASTM D256
Hydrostatic Design Basis	10.0 MPa	1450 psi	MRS Classified; ISO 9080

Mechanical Properties	Metric	English	Comments
Thermal Properties	Metric	English	Comments
Brittleness Temperature	<= -60.0 Â°C	<= -76.0 Â°F	ASTM D746

Descriptive Properties	Value	Comments
Color	Natural	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China