

SCG Chemicals EL-Leneâ„¢ H1000PWI High Density Polyethylene Pipe Resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Pipe Grade

Material Notes:

Key Characteristics: Good processing, high thermal stability, good resistance to weathering, reduce heat conductivity to

waterRecommended Applications: Above ground pipes, double wall pipesInformation provided by SCG Chemicals

Order this product through the following link:

http://www.lookpolymers.com/polymer_SCG-Chemicals-EL-Lene-H1000PWI-High-Density-Polyethylene-Pipe-Resin.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.966 g/cc	0.966 g/cc	ISO 1183
Environmental Stress Crack Resistance	>= 10000 hour	>= 10000 hour	F0; ASTM D1693
Oxidative Induction Time (OIT)	>= 70 min @Temperature 200 Å°C	>= 70 min @Temperature 392 Å°F	ISO/TR10837
Melt Flow	0.25 g/10 min @Load 5.00 kg, Temperature 190 Å°C	0.25 g/10 min @Load 11.0 lb, Temperature 374 Å°F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	64	64	ASTM D2240
Tensile Strength at Break	34.0 MPa	4930 psi	Crosshead speed 100 mm/min; ISO 527
Tensile Strength, Yield	22.0 MPa	3190 psi	Crosshead speed 100 mm/min; ISO 527
Elongation at Break	750 %	750 %	Crosshead speed 100 mm/min; ISO 527
Flexural Modulus	1.20 GPa	174 ksi	ASTM D790
Izod Impact, Notched	1.96 J/cm @Temperature -20.0 Å°C	3.67 ft-lb/in @Temperature -4.00 Å°F	ASTM D256
	2.94 J/cm @Temperature 0.000 Å°C	5.51 ft-lb/in @Temperature 32.0 Å°F	ASTM D256
	3.24 J/cm @Temperature 23.0 Å°C	6.06 ft-lb/in @Temperature 73.4 Å°F	ASTM D256

Thermal Properties	Metric	English	Comments
Brittleness Temperature	<= -60.0 Â°C	<= -76.0 Â°F	ASTM D746

Descriptive Properties	Value	Comments
Carbon Black/Pigment Dispersion (grade)	<3	ISO 18553
Color	White	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China