

SCG Chemicals EL-Leneâ,,ç LD2305F Low Density Polyethylene Film

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Film Grade

Material Notes:

Key Characteristics:Excellent clarity and glossGood zip formationContains 1000 ppm slip agent and 500 ppm antiblocking agentRecommended Applications:Zip bagsGeneral purpose film for food packagingInformation provided by SCG Chemicals

Order this product through the following link:

http://www.lookpolymers.com/polymer_SCG-Chemicals-EL-Lene-LD2305F-Low-Density-Polyethylene-Film.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.923 g/cc	0.923 g/cc	ASTM D1505
Thickness	38.0 microns	1.50 mil	
Melt Flow	3.5 g/10 min @Load 2.16 kg, Temperature 190 Â°C	3.5 g/10 min @Load 4.76 lb, Temperature 374 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, TD	9.00 MPa	1310 psi	ASTM D882
Film Elongation at Break, MD	300 %	300 %	ASTM D882
Film Elongation at Break, TD	550 %	550 %	ASTM D882
Secant Modulus, MD	0.260 GPa	37.7 ksi	ASTM D882
Secant Modulus, TD	0.250 GPa	36.3 ksi	ASTM D882
Elmendorf Tear Strength, MD	15.7 g/micron	400 g/mil	ASTM D1922
Elmendorf Tear Strength, TD	10.8 g/micron	275 g/mil	ASTM D1922
Dart Drop	2.10 g/micron	53.3 g/mil	ASTM D1709
Dart Drop Test	78.0 g	0.172 lb	ASTM D1709
Film Tensile Strength at Break, MD	24.0 MPa	3480 psi	ASTM D882
Film Tensile Strength at Break, TD	19.0 MPa	2760 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Melting Point	110 Â°C	230 Â°F	ASTM D2117
Vicat Softening Point	92.0 Â°C	198 Â°F	ASTM D1525
Brittleness Temperature	<= -73.0 Â°C	<= -99.4 Â°F	ASTM D746

Optical Properties	Metric	English	Comments
Haze	5.0 %	5.0 %	ASTM D1003
Gloss	78 %	78 %	ASTM D2457

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China