

## SCG Chemicals EL-Leneâ,,ç M70 Butene (C4) Rotational Molding Resin

Category : Polymer , Thermoplastic

### Material Notes:

Color compound resin available in pellet / powder form  
 Key Characteristics: High flow, Fast cycle times, Excellent surface finishing, Typical Applications: Complex/Intricate products, high volume/short cycle time products, such as flower pots, dolls, display stands, and decorative items  
 Information provided by SCG Chemicals

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SCG-Chemicals-EL-Lene-M70-Butene-C4-Rotational-Molding-Resin.php](http://www.lookpolymers.com/polymer_SCG-Chemicals-EL-Lene-M70-Butene-C4-Rotational-Molding-Resin.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.935 g/cc	0.935 g/cc	ASTM D1505
Melt Flow	7.0 g/10 min @Load 2.16 kg, Temperature 190 Â°C	7.0 g/10 min @Load 4.76 lb, Temperature 374 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	19.0 MPa	2760 psi	ASTM D638
Elongation at Break	800 %	800 %	ASTM D368
Flexural Modulus	0.650 GPa	94.3 ksi	ASTM D790
Dart Drop Total Energy	2.00 J/cm @Thickness 5.00 mm, Temperature -40.0 Â°C	0.00375 ft-lb/mil @Thickness 0.197 in, Temperature -40.0 Â°F	ARM Method

Thermal Properties	Metric	English	Comments
Melting Point	124 Â°C	255 Â°F	ASTM D2117
Crystallization Temperature	110 Â°C	230 Â°F	ASTM D2117

Descriptive Properties	Value	Comments
Food Contact Approved	FDA	
Heavy Metal Free (Base Resin)	Yes	
Peak Internal Air Temperature	180Â°C	TPE Method
Shrinkage Level	small	TPE Method
UV Stabilizer	UV-8 & Low UV	ASTM G155

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**